

# CRYLANE

- Good covering properties
- Roller or brush application

## DECORATIVE COATING



### DEFINITION

Acrylic decorating paint for exterior and interior surfaces

### FINISH APPEARANCE

- Mat

### SUBSTRATES

#### SUITABLE SUBSTRATES

- Bare hydraulic binder-based substrates.

#### UNSUITABLE SUBSTRATES

- Exposed horizontal substrates inclined by more than 10° from the vertical.

### SPECIFICATIONS

- Appearance: Oily liquid, white or coloured according to the colour chart.
- Composition: acrylic styrene copolymer in dispersion.
- Apparent density: 1.4 kg/dm<sup>3</sup>.
- Dilution: water.
- Solids by weight: 63 % ± 2 %.

#### Classification

- NFT 36005 Family I class 7 b<sub>2</sub>.

### INSTRUCTIONS

Should comply with this data sheet and DTU 59.1

#### Substrate preparation

- The condition and quality of substrates should satisfy the requirements defined according to the nature of the materials in DTU 59.1.

#### Tools

- Roller or brush.
- Tool cleaning: with water after application.

#### Product preparation

- Mix the product carefully in the bucket to homogenise it.

### APPLICATION

- Apply CRYLANE with a brush or roller in 2 coats.
- Dilute the 1st coat with up to 40% of water by volume.
- The 2<sup>nd</sup> coat is applied after the 1st is dry. It should be less diluted than the 1st coat.
- CRYLANE is dry after ± 6 hours and can be covered after 24 hours approx. (at + 20°C and 65% R.H).

### INSTRUCTIONS FOR USE

- Product for trade use.
- Do not apply to substrates that are frozen or when there is a risk of frost, or on wet substrates, in rainy or foggy weather, or in high dry winds.
- Application temperatures: + 5°C; over + 30°C take special precautions.

### CONSUMPTION

- 0.3 to 0.5 kg/m<sup>2</sup> per undiluted coat.  
*Actual consumption can vary according to the state of the substrates and the conditions of application.*

### PACKAGING

5 kg bucket.  
20 kg bucket.

### SHELF LIFE

12 months from the date of manufacture in its original packaging, unopened, and stored protected from the damp.

### WARRANTY

- Manufacturer's P.L.

### REFERENCE DOCUMENTS

- NF T 36005 standard.
- DTU 59.1.

The purpose of this data sheet is to provide information on the properties of the product. The information herein is based on our current knowledge. It is up to the user to check on the suitability of the product for the desired usage and to check whether this sheet has been replaced by a more recent edition.

**TECHNICAL ASSISTANCE:** ParexGroup S.A. provide information and assistance to companies that request it for starting a project in order to clarify specific requirements for the implementation of the product (or process). This assistance cannot be assimilated into either the design stage of the project, or the acceptance of the substrates, or to a check on the implementation rules.

2012 Technical Documentation

PAREXGROUP S.A. / Facade Department - 19 place de la Résistance - 92446 Issy les Moulineaux Cedex  
Tel. (33) 01 41 17 45 45 - Fax (33) 01 41 17 19 55

**PAREXLANKO**