



VG 62 FAST

OIL AND POLYURETHANE VARNISH

A fast drying oil and polyurethane clear varnish which offers a hard and durable finish.

For best results on bare timber apply two coats of BRAVA IMPREGANTE or BRAVA VG 61 DEFENDER by brush first.

A minimum of 5 total coats of VG 62 FAST are to be applied in total, making sure the first two coats are diluted 40% with white spirit and the final coats applied undiluted.

'Denibbing' using P320 paper between each coat is recommended. For previously coated timber two coats of undiluted VG 62 FAST should be applied after a light rub down using P320 paper.

The surface must be clean, dry and free from any dust prior to application.

Stir the product gently and slowly before the application.

When painting in the open-air, the coat must be dry before nightfall.



thinner:	white spirit"
coverage:	20 MQ/LT
touch drying:	3 h
overcoating:	12 h.
viscosity:	90 sec. (Ford)
suggested n° coats:	4/5
dry film thickness:	120 microns
solids content:	53%
flash point:	37° C.
specific weight:	0,86
airless:	30/1 - 0.017 - 0.019
spry:	2 - 3 Kg/cm ² - 1.2 - 1.4

AVAILABLE:

glossy 500 ml tin
glossy 1 liter tin
glossy 2,5 liters tin
satin 500 ml tin
satin 1 liter tin
satin 2,5 liters tin

U.K. Importer:



MARINE & INDUSTRIAL LLP,
Station Road, Worstead, North Walsham, NR28 9RZ.
Tel: 01692 406822. Fax: 01692 406866.
sales@marineindustrial.co.uk

