

## Epifanes Accelerator for Paint & Varnish

**Additive to reduce the open time of traditional paints & varnishes**

<b>Type</b>	Air drying	
<b>Base</b>	Wood oil	
<b>Fields of application</b>	<b>General:</b> Additive for traditional one-component paints and varnishes.	
	<b>For exterior use:</b>	add no more than 5-7%. This will not affect the gloss, elastic and longevity of the paint or varnish.
	<b>For interior use:</b>	i.e. on chairs, tables, floors, etc. up to 50% can be added to Epifanes Clear Gloss Varnish for a harder, scratch resistant finish.
	<b>Used pure:</b>	As sealer for resinous wood, bleeding pigments and for 2-3 coats per day can be applied on natural wood where a slight yellowing is less important.
<b>Colour</b>	Yellowish Transparent	
<b>Gloss</b>	High gloss	
<b>Density</b>	0,90kg/dm <sup>3</sup>	
<b>Viscosity</b>	40 seconds DIN-cup 6 mm.	
<b>Solids contents</b>	58 +/- 2 vol. %	
<b>VOC - level</b>	375 grams/liter	
<b>Packing</b>	500ml. - 1000ml.	
<b>Shelf life</b>	In closed container stored in a dark location between 5-25°C., approx. 3 years.	
<b>Conditions during application and drying</b>	Temperature	minimal 8°C. - maximum 30°C.
	Relative air humidity	minimal 50% - maximum 75%
<b>Thinner for brush applications</b>	Epifanes Brushthinner for Paint & Varnish	
<b>Thinner for spray applications</b>	Epifanes Spraythinner for Paint & Varnish	
<b>Application</b>	Do not use wet-on wet	
<b>Application tools</b>	Soft, longhaired brush (oval or full style) Conventional air spray	
<b>Theoretical coverage (pure product)</b>	18m <sup>2</sup> per litre @ 30 µm dry filmthickness	
<b>Practicle coverage</b>	Dependent on application	