

Epifanes TDA

Through drying additive

Description	Through drying additive for traditional paints and varnishes
Type	Solvent base additive
Properties	Specially formulated to speed up the through drying of Epifanes traditional one-component paints and varnishes when applied at low temperatures, allowing sanding the next day.
Field of application	Epifanes traditional one-component paints, primers and varnishes: <ul style="list-style-type: none"> In primers Epifanes Undercoat - Epifanes Multi Marine Primer Werdol Woodprimer - Werdol Metalprimer In paints Epifanes Yacht Enamel - Werdol Coasterpaint Epifanes Multiforte In varnishes Epifanes Clear Varnish - Epifanes Woodfinish Gloss
Colour	clear
Density	1,060kg/dm ³
Viscosity	Not applicable
Solids contents	70 ± 2 vol. %
VOC - level	314 grams/litre
Packing	500 ml.
Shelf life	In closed container stored in a dark location between 5 - 25°C., approx. 1 year
Recommended additions:	Application and drying at 8°C. : max. 12% Application and drying at 10°C. : max. 10% Application and drying at 15°C. : max. 5% <p>As long as the maximum additions are not exceeded, flow, gloss and outdoor durability will not be affected.</p>
Product notes	This product is not intended to shorten overcoating times. Nor is it intended to apply more wet film than advised. Once Epifanes TDA has been added to paint or varnish, pot life of the mixture is reduced to 4 hours (18°C.). Do not use above 15°C. Do not exceed dosage. All use and dosage other than specified and advised is at users risk.
Safety	The user of this product should obey all national laws and legislation concerning health, safety and environmental hazard. For more information on health and safety, refer to the Material Safety Data Sheet of this product.

Although the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unintended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. Heeren & Zoon's control. All such risks are assumed by user.

DISCLAIMER OF WARRANTIES. Seller makes no express warranties. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. In the event a warranty is created by law, buyer's EXCLUSIVE REMEDY shall be the replacement of any defective product. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or any other incidental or consequential loss) shall be available to buyer.