

Megaprimer Lite

Product description

This is a two component polyamide cured epoxy coating. Designed as a fast drying, sandable finishing primer. Can be used as primer as a part of a complete system in atmospheric and immersed environments.

Typical use

Exterior and interior areas, including hulls, above and below waterline, superstructures and decks. To be used as finish primer under Megagloss range of products. Suitable for properly prepared carbon steel, stainless steel, aluminum, composite and coated surfaces as epoxy systems and polyurethane systems. Can be used as primer or sealer for fillers in atmospheric and immersed environments.

Colours

grey, white

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	51 ± 2 %
Gloss level (GU 60 °)	ISO 2813	matt (0-35)
Flash point	ISO 3679 Method 1	25 °C
Density	calculated	1,24 kg/l
VOC-US/Hong Kong	US EPA method 24 (tested)	440 g/l
VOC-EU	IED (2010/75/EU) (calculated)	456 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.

All data is valid for mixed paint.

Gloss description: According to Jotun Performance Coatings' definition.

Film thickness per coat

Typical recommended specification range

Dry film thickness	50 - 75	µm
Wet film thickness	100 - 150	µm
Theoretical spreading rate	10,2 - 6,8	m ² /l

Surface preparation

To secure lasting adhesion to the subsequent product all surfaces shall be clean, dry and free from any contamination.

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	St 3 (ISO 8501-1)	Sa 2½ (ISO 8501-1)
Stainless steel	The surface shall be machine abraded with non-metallic abrasives or bonded fibre machine to impart a scratch pattern of min. 45 microns to the surface and to remove all polish from the surface.	Abrasive blast cleaning to achieve a surface profile using approved non-metallic abrasive media which is suitable to achieve a sharp and angular surface profile.
Aluminium	The surface shall be hand or machine abraded with non-metallic abrasives or bonded fibre machine or hand abrasive pads to impart a scratch pattern to the surface and to remove all polish from the surface.	Abrasive blast cleaning to achieve a surface profile using approved non-metallic abrasive media which is suitable to achieve a sharp and angular surface profile.
Shop primed steel	Sa 2 (ISO 8501-1)	Sa 2 (ISO 8501-1)
Galvanised steel	The surface shall be clean, dry and appear with a rough and dull profile.	The surface shall be clean, dry and appear with a rough and dull profile.
Coated surfaces	<p>New Jotun Megayacht epoxy primer: Clean, dry and undamaged compatible coating (ISO 12944-4 6.1) Remove any contamination that could interfere with the intercoat adhesion.</p> <p>Cured Jotun Megayacht epoxy primer or polyurethane topcoat: Exceeding maximum recoat intervals will require cleaning/abrading by orbital sanding or hand sanding with aluminium oxide or silicon carbide sand paper with grit P120-P160, and/or application of additional coats, depending on condition.</p> <p>Fillers: Orbital sanding or hand sanding with aluminium oxide or silicon carbide sand paper with grit P100-P160.</p>	<p>New Jotun Megayacht epoxy primer: Clean, dry and undamaged compatible coating (ISO 12944-4 6.1) Remove any contamination that could interfere with the intercoat adhesion.</p> <p>Cured Jotun Megayacht epoxy primer or polyurethane topcoat: Exceeding maximum recoat intervals will require cleaning/abrading by orbital sanding or hand sanding with aluminium oxide or silicon carbide sand paper with grit P120-P160, and/or application of additional coats, depending on condition.</p> <p>Fillers: Orbital sanding or hand sanding with aluminium oxide or silicon carbide sand paper with grit P100-P160.</p>
Composite	<p>Polyester based composites must be fully cured before initiating the surface preparation.</p> <p>The surface shall be hand or machine abraded with non-metallic abrasives or bonded fibre machine or hand abrasive pads with grit P100-P160 to impart a scratch pattern to the surface and to remove all polish from the surface.</p>	<p>Polyester based composites must be fully cured before initiating the surface preparation.</p> <p>The surface shall be hand or machine abraded with non-metallic abrasives or bonded fibre machine or hand abrasive pads with grit P100-P160 to impart a scratch pattern to the surface and to remove all polish from the surface.</p>
Galvanised steel	The surface shall be clean, dry and appear with a rough and dull profile.	The surface shall be clean, dry and appear with a rough and dull profile.

Application

Application methods

The product can be applied by

Spray:	Use air spray or airless spray. Care must be taken to achieve the specified dry film thickness.
Brush:	Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.
Roller:	May be used for small areas. Not recommended for first primer coat. Care must be taken to achieve the specified dry film thickness.

Product mixing ratio (by volume)

Megaprimer Lite Comp A	4 part(s)
Megaprimer Comp B	1 part(s)

Thinner/Cleaning solvent

Thinner:	Jotun Thinner No. 17
----------	----------------------

Guiding data for airless spray

Nozzle tip (inch/1000):	15-21
Pressure at nozzle (minimum):	150 bar / 2100 psi

Guiding data for air spray

Nozzle tip (inch/1000):	1.2-1.4
Pressure at nozzle (minimum):	2.5-3 bar

Drying and Curing time

Substrate temperature

10 °C 23 °C 40 °C

Comp A + Comp B

Surface (touch) dry	2 h	1 h	30 min
Walk-on-dry	14 h	6.5 h	3 h
Dry to over coat, minimum	24 h	12 h	9 h
Dried/cured for service	14 d	7 d	3 d

Comp A + Comp B + Thinner

Surface (touch) dry	2.5 h	1.5 h	45 min
Walk-on-dry	20 h	9 h	4 h
Dry to over coat, minimum	30 h	16 h	12 h
Dried/cured for service	14 d	7 d	3 d

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Drying time will increase with increasing film thickness.

When product is diluted to help spraying with conventional spray equipment, it is required to allow to dry for 48 hours and dry sand the surface with P220/P320.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The shortest time allowed before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Paint temperature	23 °C
Induction time	30 min
Pot life	8 h

Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	140 °C
Immersed, sea water	50 °C	60 °C

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Note that the coating will be resistant to various immersion temperatures depending on the specific chemical and whether immersion is constant or intermittent. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat:	epoxy, polyurethane
Subsequent coat:	epoxy, polyurethane

Packaging (typical)

Volume (litres)	Size of containers (litres)
--------------------	--------------------------------

Megaprimer Lite Comp A	4 / 16	5 / 20
Megaprimer Comp B	1 / 4	1 / 5

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

Megaprimer Lite Comp A	24 month(s)
Megaprimer Comp B	48 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Colour variation

When applicable, products primarily meant for use as primers or antifouling may have slight colour variations from batch to batch. Such products may fade and chalk when exposed to sunlight and weathering.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

Technical Data Sheet

Megaprimer Lite

