

CAF[®] 4

Flexible adhesive for performance assembly

Description

CAF 4 is a one component silicone elastomer which cures at room temperature:

- Acetic
- Self-levelling
- Off-white

Examples of applications

CAF 4 is mainly used in industrial sealing, bonding and coating applications:

It is notably used for:

- bonding of plastics in aeronautics,
- electrical insulation,
- coating of fabrics for thermal protection,
- coating of conveyor belts.

Advantages

CAF 4 is quick curing, has very good mechanical properties, good heat stability and high dielectric properties.

CAF 4 therefore provides perfect assembly and complete sealing between different materials subject to thermal stresses

Characteristics

1. Processing / Curing

1.1. Processing:

Processing is particularly easy, since the products are delivered ready to use. Application can be carried out either manually or using robotic application equipment.

CAF 4 is applied to one of the two joint surfaces and assembled before the product has formed a skin.

It is recommended to apply **CAF 4** to clean and dry surfaces.

CAF 4 is coated using a spray gun after having been diluted in white spirit or cyclohexane. The ideal viscosity for this is 1000 mPa.s.

1.2. Curing:

CAF 4 starts curing as soon as the products come into contact with atmospheric moisture.

Skin formation time*, min. approx 10

Time required to cure 2 mm*, hours, approx 5

Cured thickness after 24 h*, mm, approx..... 4.5

* Temperature 23 °C, relative humidity 50%.

The curing rate increases with temperature and hygrometry.

2. Properties before curing

Appearance..... viscous flowing paste

Colour..... off-white

Odour acetic

Flowability, in min..... 4
(Standards MIL S 880-2-D, NMRPS 459)

Brookfield viscosity, mPa.s 250 000
(Standards NF T 76105, ASTM D 445)

Specific gravity at 25 °C 1.16
(Standards ISO R 1183, DIN 53479, NMRPS 703)

3. Cured product properties

3.1. Specific gravity at 25 °C 1.19
(Standards ISO 2781, ASTM D 297, BS 903 part. A1)

3.2. Mechanical properties after 7 days at room temperature:

Shore A hardness..... 37
(Standards ISO R 868, DIN 53505, ASTM D 2240
BS 903 Part A7, NF T 46003, NMRPS 471)

Modulus at 100 % elongation, MPa .. 0.8
(Standards ISO R 37 (H2), DIN 53504, ASTM D 412
BS 903 Part A2, NF T 46002 (H2), NMRPS 470)

Tensile strength, MPa ... 3.8
(Standards ISO R 37 (H2), DIN 53504, ASTM D 412
BS 903 Part A2, NF T 46002 (H2), NMRPS 470)

Elongation at break, % 290
(Standards ISO R 37 (H2), DIN 53504, ASTM D 412
BS 903 Part A2, NF T 46002 (H2), NMRPS 470)

Tear strength, kN/m 4.5
(Standards ASTM D 624 specimen A, NMRPS 492)

3.3. Thermal properties:

- Lower usage temperature limit

Brittle point: - 65°C

Temperature range in continuous use
(on a 2 mm thick film, 1000 h): - 60 °C to + 225 °C

- Maximum peak recommended temperature: + 250 °C
(on a 2 mm thick film, 72 h)

N.B: These values are not absolute limits, but the range within which variations in mechanical properties are not reduced by more than 50 %.

In the case of exposure for periods shorter than 72 h, the product withstands higher

CAF® 4

peak temperatures.

3.4. Adhesion properties:

- on aluminium AG3
(1 mm thick joint, curing 7d at 23 °C, NMRPS 748)

Shear strength, MPa 1.2

Type of failure.. cohesive

- on other surfaces:

Self adhesion on glass, enamel, ceramics, epoxy paint.

Adhesion with primer:

- on polar plastics primer PM 820 or PP 878
- on stainless steel primer 131 or PM 820
- on other metals primer 131 or PM 820

3.5. Thermal conductivity:

- Thermal conductivity at 30 °C, W/m.K..... 0.30
(Standard NF x 10021)

3.6. Dielectric properties:

Dielectric strength, kV/mm 21
(Standards NF C 26225, ASTM D 419, IEC 243)

Dielectric constant at 1 MHz 2.9
(Standards NF C 26230, ASTM D 150, IEC 250)

Power factor at 1 MHz $2 \cdot 10^{-3}$
(Standards NF C 26230, ASTM D 150, IEC 250)

Volume resistivity, $\Omega \cdot \text{cm}$ $1 \cdot 10^{15}$
(Standards NF C 26215, ASTM D 257, IEC 193)

Packaging

- 100 g tubes on pallets of 1600 units.
- 25 kg tins on pallets of 10 units.
- 230 kg drums on pallets of 4 units.

Storage and shelf life

When stored in its original unopened packaging at a temperature of between + 2 °C and + 30 °C, **CAF 4** can be used for up to 24 months from its date of manufacture (expiry date).

Comply with the storage instructions and expiry date marked on the packaging.

Past this date, Bluestar Silicones no longer guarantees that the product meets the sales specifications.

Safety


Consult the safety data sheet for **CAF 4**.

CAF[®] 4


Visit our website www.bluestarsilicones.com

 **EUROPE**


Bluestar Silicones France
 21 Avenue Georges
 Pompidou
 F69486 Lyon Cedex 03
 FRANCE
 Tel. (33) 4 72 13 19 00
 Fax (33) 4 72 13 19 88

 **NORTH AMERICA**

Bluestar Silicones USA
 2 Tower Center
 Boulevard
 Suite 1601
 East Brunswick, NJ
 08816-1100
 United States
 Tel. (1) 732 227-2060
 Fax. (1) 732 249-7000

 **LATIN AMERICA**

*Bluestar Silicones
 Brazil Ltda.*
 Av. Maria Coelho
 Aguiar, 215
 Bloco G - 1º andar
 05804-902-Sao Paulo -
 SP- Brazil
 Tel. (55) 11 37477887

 **ASIA PACIFIC**

*Bluestar Silicones Hong
 Kong*
 Trading Co. Ltd
 29th Floor, 88 Hing Fat
 Street
 Causeway Bay
 Hong Kong
 Tel. (852) 3106 8200
 Fax (852) 2979 0241

Warning to the users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. BLUESTAR SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and BLUESTAR SILICONES is at their disposal to supply any additional information.