



Tel: 01380 734510
Fax: 01380 734511
Email: Sales@tym.co.uk

GASKET PAPERS – SHELF LIFE

The shelf life of FLEXOID and other related gasket materials supplied by TYM Seals & Gaskets Ltd can be regarded as 5 years, provided the following precautions are taken:

- The gasket material should be stored and cut under reasonably controlled environmental conditions. We would recommend temperatures of 10°C to 20°C and relative humidity of 50% to 65%.
- The material in roll form should be stored in its polythene bag and cut gaskets should be kept in moisture-proof wrapping or packaging. This will ensure that the product does not dry out or absorb too much atmospheric moisture.