

Material Data Sheet

Material Reference

0428

Colour

BLACK

To Specification

COMMERCIAL FINE RIBBED MATTING

Basic Properties	Value	Test Method	Unit
Base Polymer Type	NR/SBR		
Indentation Hardness	Not Specified	None	Degrees
Specific Gravity	1.5 +/- 0.05	ASTM D792	g/cm3
Tensile Strength - Minimum	2.8	ASTM D412	Mpa
Elongation @ Break - Minimum	250	ASTM D412	%
Minimum Continuous Working Temperature	-20		QC
Maximum Continuous Working Temperature	70		QC
Maximum Intermittent Working Temperature	90		QC
Compression Set 70 Degrees 22 Hours	30% Max	ASTM D395 Method B	%
Insertion Type	None		

Guidelines for Use (It is the Customers responsibility to ensure suitability of Use)

Food Use Suitability	<i>Not Reccomended</i>
Abrasion Resistance	<i>Moderate</i>
Ozone Weather Resistance	<i>Not Reccomended</i>
Flame Retardency	<i>Not Reccomended</i>
Electrical Resistance	<i>Not Reccomended</i>
General Purpose	<i>Excellent</i>

Additional Information

General Purpose Fine Ribbed Matting

Important Information about the Data provided on this Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supercedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.