



**Tel: 01380 734510**  
**Fax: 01380 734511**  
**Email: Sales@tym.co.uk**

**REINFORCED SILICONE SHEET DATA SHEET**

<b>PROPERTIES</b>	<b>1564-1711-69</b>
<b>SPECIFICATION</b>	AMS 3320
<b>THICKNESS</b>	1.5MM, 3.0MM, 6.0MM
<b>FIBERGLASS STYLE</b>	1564
<b>FIBREGLASS THICKNESS</b>	0.014
<b>BREAK STRENGTH</b>	300 PPI
<b>BURST STRENGTH</b>	750 PSI
<b>DUROMETER SHORE A</b> (actual rubber is 50 shore)	1.5mm=74 shore 3.0mm=65 shore 6.0mm=60 shore
<b>COMPRESSION MODULUS</b> (5%), PSI	1.5mm=100 3.0mm=90 6.0mm=80
<b>TEMPERATURE</b>	-65 <sup>0</sup> F TO 500 <sup>0</sup> F

ROLL SIZE ARE 1MTR WIDE X 10MTR ROLLS  
 RED OXIDE

*The above results relate only to the samples tested and therefore the information given here should be used as a guide only*