



Tel: 01380 734510
Fax: 01380 734511
email: sales@tym.co.uk

SPECIFICATION SHEET

SILICONE SPONGE EXTRUDED SECTIONS

SPECIFICATION	DETAIL	TEST
Density	16lbs per cubic ft	
Brittle Point	-80°C (-112°F)	ASTM D746
Limiting Oxygen Index	24%	BS 2872 PART 1
Thermal Conductivity	6.4 x 10(-2sq) W.m(-1)	BS 874 PART 2
Radiation Resistance	>10(5) GRAYS (10(7) RADS TYPICAL	
Toxicity (NES 713 ISS 3)	14 N/MM	
Smoke Index (NES 711)	46	
Burn Rate (BS4735)	0.03MM PER SECOND	
Thermal Value	0.0695 W (M.K)	

Note: The above results relate only to the samples tested and therefore the information given here should be used as a guide only.

Further information:

The thermal stability of silicone rubber is probably its most important asset. Components made from these rubbers are affected only to a small extent by extremes of temperature, ranging from -90°C to +250°C (depending on grade). Even at temperatures as high as +300°C silicone rubber will operate for limited periods.

Silicone rubber is an excellent electrical insulating material. Its resistance to arcing, corona, ultra violet light and ozone is good. It decomposes at 400°C to 500°C leaving an inert, non-flammable and electrically non-conductive residue.

The silicone sponge sheet and sections supplied by TYM is made of a fine cellular construction composed mainly of non-interconnecting cells and is normally an off-white colour.

There are many applications for the sheeting and sections but for continuous use it will withstand temperatures between -60°C and +200°C.

The above information is believed to be correct but does not purport to be all inclusive. As individual operating conditions influence the application of each product, the information in this data sheet can only be seen as a guide. It is the sole responsibility of the customer to evaluate his individual requirements, particularly whether the specified properties of our products are sufficient for his intended use.