

H-LaF10L	788475	$n_d = 1.78800$	$v_d = 47.49$	$n_F - n_C = 0.016592$
		$n_e = 1.79195$	$v_e = 47.26$	$n_{F'} - n_{C'} = 0.016758$

折射率 Refractive Indices			相对部分色散 Relative Partial Dispersions				内透射比 Internal Transmittance		
	λ (nm)		$P_{d,c}$	0.3012	$P'_{d,c'}$	0.2510	λ (nm)	τ 5 mm	τ 10 mm
n_t	1014.0	1.76996	$P_{e,d}$	0.2381	$P'_{e,d}$	0.2358	2400	0.83	0.69
n_r	706.5	1.78018	$P_{g,F}$	0.5550	$P'_{g,F'}$	0.4923	2200	0.960	0.922
n_c	656.3	1.78300					2000	0.986	0.972
$n_{c'}$	643.8	1.78379	化学稳定性 Chemical Properties				1800	0.997	0.995
n_{He-Ne}	632.8	1.78453			Grade		1600	0.999	0.998
n_D	589.3	1.78785	RC(S)		1		1400	0.999	0.998
n_d	587.6	1.78800	RA(S)		3		1200	0.999	0.998
n_e	546.1	1.79195	D_W		1		1060	0.999	0.998
n_F	486.1	1.79959	D_A		3		1000	0.999	0.998
$n_{F'}$	480.0	1.80055					950	0.999	0.998
n_g	435.8	1.80880	热性质 Thermal Properties				900	0.999	0.998
n_h	404.7	1.81657	T_g (°C)		662		850	0.999	0.998
n_i	365.0	1.83007	T_s (°C)		697		800	0.999	0.998
			$T_{10}^{14.5}$ (°C)		620		700	0.999	0.998
			T_{10}^{13} (°C)		646		650	0.998	0.997
			$T_{10}^{7.6}$ (°C)		743		600	0.998	0.997
			$\alpha_{20/120^\circ C}(10^{-7}/K)$		62		550	0.997	0.995
			$\alpha_{100/300^\circ C}(10^{-7}/K)$		70		500	0.996	0.993
			λ (W/m·K)				480	0.995	0.991
							460	0.993	0.987
色散公式的系数			机械性质 Mechanical Properties				440	0.991	0.983
Constants of Dispersion Formula			H_K (10^7 Pa)		795		420	0.988	0.977
A_0	3.1178002		F_A				400	0.981	0.963
A_1	$-1.2680088 \times 10^{-2}$		E (10^7 Pa)		12223		390	0.973	0.947
A_2	2.9052225×10^{-2}		G (10^7 Pa)		4727		380	0.960	0.921
A_3	$-3.8643945 \times 10^{-4}$		μ		0.293		370	0.936	0.877
A_4	1.2045644×10^{-4}		B (10^{-12} /Pa)				360	0.90	0.81
A_5	$-4.4702446 \times 10^{-6}$						350	0.84	0.70
			其他性质 Other Properties				340	0.74	0.55
			ρ (g/cm ³)		4.56		330	0.59	0.35
							320	0.35	0.12
							310	0.07	
							300		
							290		
							280		
							着色度 Color Code		
							λ_{80}/λ_5	39/32	
折射率温度系数 Temperature Coefficient of Refractive Index									
温度范围(°C) Temperature Range	dn/dt rel(10⁻⁶/°C)								
	t	C'	d	e	F'	g			
-40~-20	2.6	3.3	3.4	3.8	4.3	5.2			
-20~0	3.4	4.0	4.4	4.5	4.7	5.5			
0~20	3.4	4.1	4.2	4.4	4.8	5.7			
20~40	3.8	4.2	4.5	4.7	5.9	6.3			
40~60	4.0	4.8	4.9	5.1	6.0	6.3			
60~80	4.1	4.8	5.1	5.3	6.0	6.4			