

D-K59	518635	$n_d = 1.51760$	$\nu_d = 63.50$	$n_F - n_c = 0.008150$
		$n_e = 1.51954$	$\nu_e = 63.40$	$n_{F'} - n_{c'} = 0.008200$

Refractive Indices			Relative Partial Dispersions				Internal Transmittance		
	λ (nm)		$P_{d,c}$	0.3092	$P'_{d,c'}$	0.2561	λ (nm)	τ 5 mm	τ 10 mm
n_t	1014.0	1.50793	$P_{e,d}$	0.2380	$P'_{e,d}$	0.2366	2400	0.900	0.81
n_r	706.5	1.51362	$P_{g,F}$	0.5360	$P'_{g,F'}$	0.4754	2200	0.933	0.87
n_c	656.3	1.51508					2000	0.987	0.975
$n_{c'}$	643.8	1.51550	Chemical Properties				1800	0.994	0.989
n_{He-Ne}	632.8	1.51587			Grade		1600	0.997	0.995
n_D	589.3	1.51753	RC(S)		1		1400	0.987	0.975
n_d	587.6	1.51760	RA(S)		1		1200	0.999	0.998
n_e	546.1	1.51954	D _W		1		1060	0.999	0.998
n_F	486.1	1.52323	D _A		1		1000	0.999	0.998
$n_{F'}$	480.0	1.52370					950	0.999	0.998
n_g	435.8	1.52760	Thermal Properties				900	0.999	0.998
n_h	404.7	1.53120	T_g (°C)		497		850	0.999	0.998
n_i	365.0	1.53732	T_s (°C)		551		800	0.997	0.995
			$T_{10}^{14.5}$ (°C)		460		700	0.997	0.994
			T_{10}^{13} (°C)		492		650	0.996	0.993
			$T_{10}^{7.6}$ (°C)				600	0.996	0.993
			$\alpha_{20/120^\circ C}(10^{-7}/K)$		65		550	0.997	0.994
			$\alpha_{100/300^\circ C}(10^{-7}/K)$		80		500	0.996	0.993
			λ (W/m · K)				480	0.996	0.992
							460	0.996	0.992
Constants of Dispersion Formula			Mechanical Properties				440	0.995	0.990
A_0	2.2704227		H_K (10 ⁷ Pa)		609		420	0.995	0.990
A_1	$-8.7648181 \times 10^{-3}$		F_A		70		400	0.995	0.990
A_2	1.3241433×10^{-2}		E (10 ⁷ Pa)		8303		390	0.994	0.988
A_3	$-5.4858082 \times 10^{-4}$		G (10 ⁷ Pa)		3424		380	0.991	0.983
A_4	9.3735842×10^{-5}		μ		0.212		370	0.989	0.979
A_5	$-4.4191155 \times 10^{-6}$		B (10 ⁻¹² /Pa)				360	0.982	0.964
							350	0.966	0.933
Deviation of Relative Partial Dispersions ΔP from the "Normal Line"			Other Properties				340	0.927	0.86
$\Delta P_{F,e}$	-0.0023		ρ (g/cm ³)		2.41		330	0.83	0.69
$\Delta P_{g,F}$	-0.0016						320	0.62	0.38
							310	0.28	0.08
							300		
							290		
							280		
							Coloration Code		
							λ_{80}/λ_5	34/31	
Temperature Coefficients of Refractive Index									
Rang of Temperature	dn/dt relative(10⁻⁶/°C)								
	t	C'	d	e	F'	g			
-40~-20	2.7	3.0	3.2	4.1	4.3	4.8			
-20~0	3.8	4.1	4.2	4.4	4.6	4.9			
0~20	4.1	4.2	4.3	4.6	4.7	4.9			
20~40	4.1	4.3	4.4	4.5	4.7	5.0			
40~60	4.0	4.3	4.4	4.5	4.7	5.1			
60~80	4.1	4.5	4.5	4.6	5.0	5.4			