
Double Tough Nitrile Gloves

PRODUCT INFORMATION				
MATERIAL	Nitrile			
COLOUR	Blue			
ТҮРЕ	Ambidextrous, non-sterile, single-use			
INTERIOR	Powder-free			
EXTERIOR	Fully textured			
SIZES	S - 3XL			
COUNTRY OF ORIGIN	Thailand			
STORAGE	Store in original packaging in a cool, dry and well ventilated area, away from dust, direct sunlight, moisture, x-ray and excessive heat above 100°F (37°C)			



PHYSICAL PROPERTIES					
AQL	1.5				
GLOVE WEIGHT	12.3grams (medium)				
GLOVE THICKNESS	8mil, min 0.22mm (finger)				
GLOVE LENGTH	300mm				
	BEFORE AGING AFTER AGIN				
TENSILE STRENGTH (MPA)	min. 21	min. 21			
ULTIMATE ELONGATION	min. 500%	min. 450%			



QUALITY STANDARDS			
FDA STATUS	(21 CFR 177) compliant for food handling		
AUDIT STANDARDS	Manufactured in an ISO 9001:2015		
TEST STANDARDS	EN ISO 374-1:2016/Type B EN ISO 374-5:2016 Resistance to Bacteria, Fungi and Viruses EN374-2:2014 Resistance to Microbial penetration EN 16523-1:2015+A1:2018 resistance to permeation by chemicals		

PACKAGING & ORDERING INFORMATION					
CODE	SIZE	PURCHASE UNIT	CARTON DIMENSIONS (LxWxH)	CARTON WEIGHT	CUBIC METRE
104020	S	1 carton of 500 Gloves (50/box x 10)			
104030	М				
104040	L		71 7 × 20 0 × 71 0 m		0.07m3
104050	XL		31.3 x 26.6 x 31.8cm	6.9kg	0.03m³
104060	2XL				
104070	3XL				

RESISTANCE OF GLOVES TO PERMEATION BY CHEMICALS

CHEMICAL	EN ISO 374-1:2016	EN 374-4:2013			
	PERFORMANCE LEVEL	MEAN DEGRADATION / %			
Sulphuric Acid 96%	1	100			
n-Heptane (J)	3	37.3			
Sodium Hydroxide 40% (K)	6	-12.2			
Ammonium Hydroxide 25% (O)	2	-8.4			
Hydrogen Peroxide 30% (P)	3	-6.6			
Formaldehyde 37% (T)	5	2.8			
EN ISO 374-1:2016 - permeation levels are based on breakthrough times as follows:					

Performance Level:	1	2	3	4	5	6
Minimum breakthrough time (Min):	>10	>30	>60	>120	>240	>480

EN 374-4:2013 - Degradation results indicate the change in puncture resistance of the gloves after exposure to the challenge chemical

Safety gloves to protect against chemicals are classified according to their permeation time (time taken for the chemical to penetrate the glove) and number of chemicals tested:

- Type A at least 30min each for at least 6 test chemicals
- Type B at least 30min each for at least 3 test chemicals
- Type C at least 10min each for at least 1 test chemicals

EN ISO 374-5:2016 - Resistance to Bacteria and Fungi = Pass, Resistance to Virus = Pass

MANDATORY STATEMENTS EN ISO 374-1:2016

"This information does not reflect the actual duration of protection in the workplace and the differentiation between mixtures and pure chemicals." "The chemical resistance has been assessed under laboratory conditions from samples taken from the palm only (except in cases where the glove is equal to or over 400mm - where the cuff is tested also) and relates only to the chemical tested. It can be different if the chemical is used in a mixture." "It is recommended to check that the gloves are suitable for the intended used because the conditions at the workplace may differ from the type depending on temperature, abrasion and degradation."

"When used, protective gloves may provide less resistance to the dangerous chemical due to changes in physical properties. Movements, snagging, rubbing, degradation caused by the chemical contact etc. may reduce the actual use time significantly. For corrosive chemicals, degradation can be the most important factor to consider in selection of chemical resistant gloves."

"The penetration resistance has been assessed under laboratory conditions and relates to the tested specimen."



Contact us today to receive samples or for more information on this product.

FEGUARD WHAT MATTERS

Eagle Protect sales@eagleprotect.co.nz eagleprotect.co.nz 0800 633 468

