

Long Cuff Nitrile Gloves




PRODUCT INFORMATION

MATERIAL	Nitrile
COLOUR	Blue
TYPE	Ambidextrous, non-sterile, single-use
INTERIOR	Powder-free
EXTERIOR	Textured
SIZES	S - 3XL
COUNTRY OF ORIGIN	Thailand
STORAGE	Store in original packaging in a cool, dry and well ventilated area, away from dust, direct sunlight, moisture, x-ray and excessive heat above 100°F (37°C)

PHYSICAL PROPERTIES

AQL	1.5	
GLOVE WEIGHT	6.3grams (medium)	
GLOVE THICKNESS	4.5mil, min 0.13mm (finger)	
GLOVE LENGTH	290mm	
	BEFORE AGING	AFTER AGING
TENSILE STRENGTH (MPA)	Min. 21	Min. 21
ULTIMATE ELONGATION	500%	450%



QUALITY STANDARDS

FDA STATUS	(21 CFR 177) compliant for food handling
AUDIT STANDARDS	Manufactured in an ISO 9001:2015
TEST STANDARDS	EN ISO 374-1:2016/Type B EN ISO 374-5:2016 Resistance to Bacteria, Fungi and Viruses Meets EN374-2:2014 Resistance to Microbial penetration

PACKAGING & ORDERING INFORMATION

CODE	SIZE	PURCHASE UNIT	CASE DIMENSIONS (LxWxH)	CARTON WEIGHT	CUBIC METRE
112020	S	1 carton of 1000 Gloves (100/box x 10)	30 x 29 x 26.4cm	8.0kg	0.03m ³
112030	M				
112040	L				
112050	XL				
112060	2XL				
112070	3XL				
BULK PACK CODE	SIZE	PURCHASE UNIT	CARTON DIMENSIONS (LxWxH)	CARTON WEIGHT	CUBIC METRE
112130	M	1 carton of 1500 Gloves (250/bag x 6)	53 x 29.2 x 27.7cm	10.5kg	0.03m ³
112140	L				
112150	XL				
112160	2XL				

RESISTANCE OF GLOVES TO PERMEATION BY CHEMICALS

CHEMICAL	EN ISO 374-1:2016 PERFORMANCE LEVEL	EN 374-4:2013 MEAN DEGRADATION / %
n-Heptane (J)	2	52.7
Hydrogen Peroxide 30% (P)	2	29.8
Sodium Hydroxide 40% (K)	6	5.8
Formaldehyde 37% (T)	4	22.5

EN ISO 374-1:2016 - permeation levels are based on breakthrough times as follows:

Performance Level:	1	2	3	4	5	6
Minimum breakthrough time (Min):	>10	>30	>60	>120	>240	>480

Safety gloves to protect against chemicals are classified according to their permeation time (time taken for the chemical to penetrate the glove) and number of chemicals tested:

- Type A - at least 30min each for at least 6 test chemicals
- Type B - at least 30min each for at least 3 test chemicals
- Type C - at least 10min each for at least 1 test chemicals

EN 374-4:2013 - Degradation results indicate the change in puncture resistance of the gloves after exposure to the challenge chemical

EN ISO 374-5:2016 - Resistance to Bacteria and Fungi = Pass, Resistance to Virus = Pass

MANDATORY STATEMENTS EN ISO 374-1:2016

"This information does not reflect the actual duration of protection in the workplace and the differentiation between mixtures and pure chemicals."
 "The chemical resistance has been assessed under laboratory conditions from samples taken from the palm only (except in cases where the glove is equal to or over 400mm - where the cuff is tested also) and relates only to the chemical tested. It can be different if the chemical is used in a mixture."
 "It is recommended to check that the gloves are suitable for the intended use because the conditions at the workplace may differ from the type depending on temperature, abrasion and degradation."
 "When used, protective gloves may provide less resistance to the dangerous chemical due to changes in physical properties. Movements, snagging, rubbing, degradation caused by the chemical contact etc. may reduce the actual use time significantly. For corrosive chemicals, degradation can be the most important factor to consider in selection of chemical resistant gloves."
 "*The penetration resistance has been assessed under laboratory conditions and relates to the tested specimen.*"



Contact us today to receive samples or for more information on this product.

Eagle Protect
 sales@eagleprotect.co.nz
 eagleprotect.co.nz
 0800 633 468

SAFEGUARD WHAT MATTERS™

