

AP 250



FAST DRY WHITE METAL PRIMER Data Sheet

DESCRIPTION: APOC® 250 Fast Dry White Metal Primer is a high penetration fast dry primer that seals and stops rust from spreading. This product contains a concentration of rust inhibitive chemicals to prevent rust from coming back. Also great for stain blocking and priming other problem areas. Use prior to applying elastomeric roof coatings.

PREPARATION: All surfaces must be dry and free of dust, dirt, oil, loose or peeling paint and all other foreign matter. Rusty metal must be cleaned with a wire brush. Pressure washing after wire brushing gives best results. MIX CONTENTS THOROUGHLY BEFORE USING. MECHANICAL MIXING RECOMMENDED.

APPLICATION: For exterior use only. Apply by brush, roller, or suitable spray equipment, avoiding coating build up or puddling.

NOTE: Application to surfaces above 110°F is not recommended.

DRY TIME: Product will dry in 2 hours in dry weather above 80°F. Humidity and/or colder weather will extend drying time. Product can be recoated immediately after drying. DO NOT APPLY WHEN HEAVY DEW OR RAIN IS EXPECTED WITHIN 2-4 HOURS.

FOR BEST RESULTS: Apply when surface temperatures are between 50°F and 110°F. In colder weather, store product in heated room (65°F to 80°F) at least 24 hours prior to application.

NOTE: Do not apply on single ply membranes such as EPDM, TPO, PVC, or Hypalon. Test small area first if there is a question of compatibility.

COVERAGE RATE: 400 sq. ft./gal.

PRECAUTIONS: Precautions should be taken to prevent odors from entering the building. When transporting this product, ensure that lid is tight and pail secure and upright. Do not allow pail to tumble as this may cause lid to loosen and leakage to occur. Do not transport on passenger seats or inside the passenger compartment of any vehicle. Store product in the cargo area of vehicle, and secure over protective cloths to prevent damage due to accidental spills. Do not store at temperatures above 110°F. Do not reuse empty containers. Do not use in drinking water or food systems. Seal container when not in use.

CLEAN-UP: Clean tools or spills with mineral spirits or paint thinner.

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS

Weight Per Gallon	11 lbs.
Residue by Evaporation	65 min.
Adhesion to Polyurethane Foam	Not Recommended
Combustible Solvents	35%
Consistency	Brush, Roller, or Spray
Cure Time (50% Relative Humidity, 70°F)	2-4 hours
Application Temperatures	50° - 110°F
Clean-up Tools	Paint Thinner, Mineral Spirits

Approx. Shipping Weights: (Note: All approx. weights include container.)

5 gallons (18.9L)	57 lbs.
55 drums (208.2L)	650 lbs.

CAUTION – COMBUSTIBLE MIXTURE CAUTION!: HARMFUL OR FATAL IF SWALLOWED. EYE, SKIN AND RESPIRATORY IRRITANT.

If swallowed DO NOT induce vomiting. Call physician immediately. In case of : Eye contact - flush with large amounts of room temperature water for 15 minutes; Skin contact - wash thoroughly with soap and water; Irregular or stopped breathing - administer oxygen, give artificial respiration and get medical attention immediately. Avoid prolonged breathing of vapor or spray mist.

FOR EXTERIOR USE ONLY
Use with adequate Ventilation
Keep Out of Reach of Children
VOC/VOS - 420 g/l max.

CALIF. PROP. 65 • CHEMICAL WARNING (CALIFORNIA HEALTH AND SAFETY CODE #25249.5 ET SEQ). WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects or reproductive harm. Use proper protection and adequate ventilation, when using product.

WARRANTY AND DISCLAIMER: To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance and is subject to change without prior notice. User must contact APOC to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Liability, if any, is limited to replacement of product unless installed by an approved contractor in accordance with APOC warranty procedures and program.

For limited warranty and disclaimer information, visit our website at:
www.apoc.com/productwarrantyinfo.

©2008 Gardner Asphalt Corporation Manufactured
by / Fabricado por: Gardner Asphalt Corporation
P.O. Box 5449, Tampa, FL 33675

See MSDS for more info



Gardner Asphalt Corporation • P.O. Box 5449 • Tampa, Florida 33675-5449
Phone: (813) 248-2101 • Fax (813) 248-6768 • www.apoc.com