



22A Main Street North, Searsmont, ME 04973

P: (207) 236-4246 / P: (866) 565-5350 / F: (207) 470-7464

info@weteffect.com / weteffect.com

# Test Report

Report No : L202002004

Feb 19,2020

Page : 1/2

Type of Tested Fabric :

FIB

Contents : 85% Polyester, 15% Spandex

Width : 60 inch ±3%

Weight : 197 g/m<sup>2</sup> ±5%

1. Textiles — Determination of fabric propensity to surface fuzzing and to pilling — Part 1: Pilling box method (ISO 12945-1, 10,800 rev.)

	Pilling Resistance
In Warp	4.0
In Weft	4.0

2. Colorfastness test

	Red	Black	Navy	Royal	Orange	Yellow
Color	001	002	007	073	223	228
ISO 105 B02(20hr), Grade	4.0	4.0	4.0	3.5	4.0	3.5
ISO 105 C06 A1S, Grade	4.0	4.0	4.0	4.0	4.0	2.5
ISO 105 E01, Grade	4.0	4.0	4.0	4.0	4.0	4.0
ISO 105 E02, Grade	4.0	4.0	4.0	4.0	4.0	4.0
ISO 105 E03(50ppm), Grade	4.5	4.0	4.0	4.5	4.5	3.5
ISO 105 E03(100ppm), Grade	4.0	4.0	4.0	4.0	4.5	3.5
ISO 105 E04(Acid), Grade		3.0				
ISO 105 E04(Alkaline), Grade		3.0				

	Silver	White	Pink	Lime	Purple
Color	238	465	817	931	Q28
ISO 105 B02(20hr), Grade	4.0	4.0	3.5	4.0	3.5
ISO 105 C06 A1S, Grade	4.0	-	4.0	3.0	4.0
ISO 105 E01, Grade	4.0	-	4.0	4.0	4.0
ISO 105 E02, Grade	4.0	-	4.0	4.0	4.0
ISO 105 E03(50ppm), Grade	4.0	4.0		4.5	
ISO 105 E03(100ppm), Grade	3.5	4.0		4.5	
ISO 105 E04(Acid), Grade					
ISO 105 E04(Alkaline), Grade					

## Test Report

Report No : L202002004

Feb 19,2020

Page : 2/2

### 3. UPF test

	Red	Black	Navy	Royal	Orange	Yellow
Color	001	002	007	073	223	228
Mean UPF	829.1	759.2	1013.3	1084.6	711.5	106.3
UPF Rating	50+	50+	50+	50+	50+	50+
Mean UVA (315-400 nm), %	0.15	0.15	0.17	0.17	0.23	1.49
Mean UVB (290-315 nm), %	0.12	0.13	0.09	0.09	0.13	1.00
UVR protection category	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
	Silver	White	Pink	Lime	Purple	
Color	238	465	817	931	Q28	
Mean UPF	1232.5	1065.7	645.3	716.2		
UPF Rating	50+	50+	50+	50+	50+	
Mean UVA (315-400 nm), %	0.17	0.12	0.35	0.25		
Mean UVB (290-315 nm), %	0.07	0.08	0.14	0.13		
UVR protection category	Excellent	Excellent	Excellent	Excellent	Excellent	

### Determination of the UVR transmission of a Dry Textile:

AS/NZS 4399-2017,Appendix A

#### Parameters:

SBW : 5.0 nm

Scan speed: 100 nm/min(Fast)

No. of Scan : 8

UV-Vis Spectrophotometer model SHIMADZU UV-2600PC

#### Solar Spectrum:

Irradiance measurements Noon on 17 Jan 1990 for Melbourne(38 degree South)

#### Remark :

- The results given apply only to the color and weight of fabric tested. Unless otherwise stated the fabric is tested dry and relaxed.
- This UPF Rating is for the fabric and does not address the amount of protection which is afforded by the design of the article. The manipulations involved in garment manufacture such as stretching and sewing may lower the UPF of the material.
- The protection offered by this fabric may be lessened
  - At points where the fabric is in close contact with the skin such as across the shoulders.
  - If the fabric is stretched and wet & with time, due to the effect of normal wear.