

TECHNICAL DATA SHEET

Flexible Polyurethane Foam ²⁵²⁸ 42/28 HR Orange

Physical Properties	Typical Data	Units	Test Method
Density	42-2.10/+6.30	Kg/m ³	ASTM D 3574-01 A
IFD25	28 ±3	Lb/50in ²	ASTM D 3574-01 B1
Support Factor (Sag Factor)	2.2 minimum	N/A	ASTM D 3574-01 X3.1
Non Flame Retardant			BT CAL-1117-2013
Color	Orange	Orange	-----

For the handling and storage it is recommended to avoid ignition sources since the material is considered like fuel. It will have to be stored in places free of humidity, the direct light of the sun and with a good ventilation. It is important to indicate that the consumer is responsible by any type for handling or inadequate storage in his facilities

Notes:

Each client is responsible to confirm that this product is adapted for its application. The information and data contained in this Technical Data Sheet are provided of good faith and some like part of the terms and conditions of sale do not constitute guarantee established by Ureblock, S.A. de C.V.

Produciendo
y

para el mundo.