

Quality - Put to the Test

Industry Leading Quality Standards

| Test | Standard | Ceramic Results | Glass Results | Conclusion |
|-----------------------------------|--|---|---|---------------------------------------|
| ASTM C1026 | | | | |
| Resistance to Freeze-Thaw Cycling | Subject to 15 cycles of freeze-thaw testing | NO visible evidence of freeze-thaw damage | NO visible evidence of freeze-thaw damage | Industry leading performance |
| ASTM C373 | | | | |
| Average Water Absorption | < 3.0% | 1.66% | < 0.5% | Vitreous / Impervious Classifications |
| ASTM C650 | | | | |
| Resistance to Pool Chemicals | Soak in test solution for 24 hrs. at 74°F | No visual effect | No visual effect | Impervious to common pool chemicals |
| ASTM C648 | | | | |
| Average Breaking Strength | > 250 lbf. | 418 lbf. | Varies | Exceeds Standard |
| ANSI A137.2-7.9 | | | | |
| Thermal Shock Resistance | Subject to 10 cycles of thermal shock immersion test | No visual effect | No visual effect | Thermal shock resistant |

The Artistry In Mosaics Guarantee – The complete range of Artistry In Mosaics products will meet or exceed these standards. Please visit www.artistryinmosaics.com/warranty for full warranty information.

Shade and size variations are inherent characteristics in all ceramic and glass tile products. These variations are a trademark of handcrafted quality and add to the unique beauty of your individual mosaic.

All pool and spa installations must conform to current Tile Council of North America installation guidelines.

All dimensions in this catalog are height x width. Please note that all images are not necessarily proportionate to each other.

All images and designs ©2003-2021 Artistry In Mosaics, Inc.



AQUABLU

Official Distributor

(800) 971 1442

www.aquablumosaics.com