



1 **When applying the Base Coat it looks streaky or seperated on the nail.**
- The nail not being correctly prepared.
Ensure the nail is buffed and cleaned of all oils by using Pro Prep & Wipe and a lint-free pad.
- Too much primer has been applied to the nail or the primer has not fully dried down.
Only a very small amount of Zero Primer should be applied to each nail and you should let it air dry for 20+ seconds before beginning your Base Coat application.
- The Base Coat is not mixed.
Shake the bottle for 20 seconds to blend the formula.

2 **There are small bubbles forming in my colour or Top Coat.**
- Too much pressure is being applied during application.
Zero Gel Polish[®] colour coats and top coat are best applied with a light hand. You should float the product over the nail rather than applying hard pressure. To smooth out the application lightly brush over the nail to a few times until all bubbles are gone.

3 **The colour is wrinkling after curing.**
- Too much product has been applied to the nail resulting in under-curing.
Zero Gel Polish[®] colour coats are very highly pigmented creamy formula. Ensure thin layers are applied to the nail using a small amount of product. The product will cover the nail in 2 coats.

4 **The Top Coat is dull after I wipe it.**
- Incorrect material/technique being used.
Some lint-free wipes may not be thick or absorbant enough to remove the tacky layer. Try using a cotton pad and Pro-Prep and Wipe solution. Ensure you are wiping the nail in a downward motion as not to spread the inhibition layer around the nail. Only use one wipe per hand.

5 **The nails are chipping/peeling within days of application.**
- The nail not being correctly prepared.
Ensure the nails have been buffed, cleansed & primed with Zero Primer to aid product adhesion.
- Base Coat applied too thick.
Ensure the Base Coat is applied thinly and worked into the nail plate.
- Under-curing of the product.
Ensure the the product has been applied in thin layers and cured as recommended in our Dual Pro UV LED lamp for 60 seconds per layer.
- Free-Edge of the nails have not been capped.
Ensure you cap the free-edge of each nail during each layer application.

FREE FROM HEMA
Di-HEMA
HPMA
TPO, IBOA

