



**TYPICAL PROPERTIES OF  
NON  
Non-Asbestos Green Compressed  
Aramid Fiber Nitrile Binder**

**FEATURES:**

- Excellent Gasketing Material

**SPECIFICATIONS MET**

ASTM-F-140 F712122A9E22K9M5

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT
COLOR	VISUAL	N/A	GREEN
COMPRESSIBILITY	ASTM-F-36A	%	7-17
RECOVERY	ASTM-F-36J	% MIN	50
TENSILE STRENGTH	ASTM-F-36J	PSI	1750
CREEP RELAXATION	ASTM-F-36J	%	25
SEALABILITY	ASTM-F-38B	ML/HR	.33
DENSITY	ASTM-F-37	LB/FT	109.18
THICKNESS INCREASES	ASTM OIL NO. 3 5 HRS @ 300 F	%	0-10
THICKNESS INCREASES	ASTM FUEL 8 5 HRS @ 73 F	%	0-10
TEMPERATURE RANGE	(°F)	DEGREES FAHRENHEIT	UP TO +500

This information is furnished as a guide for selecting materials. SAS Industries, Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.