



**TYPICAL PROPERTIES OF
SBR
Red Rubber (SBR), 75A Durometer**

DESCRIPTION:

Styrene Butadiene (SBR) also commonly referred to as Red Rubber is a synthetic rubber.

FEATURES:

- Excellent Gasketing Material

SPECIFICATIONS MET

ASTM-D-1330-66 Class 1

POLYMER:

Polychloroprene

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT
COLOR	VISUAL	N/A	Red
DUROMETER, SHORE "A"	ASTM-D-2240	POINTS	75 ± 5
SPECIFIC GRAVITY	ASTM-D-297	G/CC	1.7
TENSILE STRENGTH	ASTM-D-412	PSI (minimum)	700
ELONGATION	ASTM-D-412	%	200
TEMPERATURE RANGE	(°F)	DEGREES FAHRENHEIT	-20 TO +170

This information is furnished as a guide for selecting materials. SAS Industries, Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.