

LCD Heater Panels



Key Features

- High optical transparency
- Low reflectance
- Precise electrical resistivity
- Thermally uniform and stable

Applications

- Avionics displays
- Ruggedized displays
- Industrial Displays

High Performance and Reliability

MAC Thin Films industry leading technology produces high transmission, low reflection, thermally stable LCD heater panels where the performance and reliability of the LCD display is a critical element in design functionality.

Our LCD heaters are manufactured in large vacuum deposition chambers where our source materials are thermally evaporated with precisely controlled layers of dielectric materials and indium tin oxide to achieve highly optimized optical and electrical properties for demanding applications.

MAC Thin Films is committed to providing our customers with the expertise needed to navigate through the design and prototyping phases. We are also committed to delivering production units with unsurpassed product performance and complemented with superior customer service.



Construction & Performance Features

• Available Substrates:

- o Clear soda lime float glass
- Corning Eagle XG[™]
- Schott Boro 33[™]
- Thickness ranges from 0.7mm to 6mm

• Coating & Mechanical Tolerancing:

- Sheet Resistivity: +/-20%
- o L x W: (0.7-1.9mm) +/-0.38mm
- L x W: (2.3-6mm) +/-0.5mm

Optical Performance (IM 16 Ω/\Box)







• Environmental & Durability Tests

- o 24-hour humidity (MIL-C-675)
- Adhesion: Snap tape (MIL-M-13508)
- Abrasion: 40 eraser rubs (MIL-C-675)

 2721 Giffen Avenue, Santa Rosa CA 95407 • P +1-707-791-1650 or www.MACThinFilms.com Copyright © 2022-2024 MAC Thin Films. All rights reserved.
Product specifications and descriptions in this document are subject to change without notice.



LCD Heater Panels



- o Salt solubility (MIL-C-675)
- Temperature resistance (MIL-C-14806)

• Typical Heater Panel Characteristics

Total Bus Bar Height (flat connector)	< 0.15 mm
Total Bus Bar Height (round AWG27 wire)	< 0.80 mm
Pull Strength	> 4N (square corner)
	> 2N (chamfer corner)
Power Density Rating	30.0 W / in ²
	4.7 W / cm ²
Thermal Uniformity	+/- 2°C

Bus Bar Options



Direct Bonding to Bus Bar



Flat Flexible Connector



 2721 Giffen Avenue, Santa Rosa CA 95407 • P +1-707-791-1650 or www.MACThinFilms.com Copyright © 2022-2024 MAC Thin Films. All rights reserved.
Product specifications and descriptions in this document are subject to change without notice.