



REEF 9730-0-PFAL

COLORWAYS	Amber, Azure, Driftwood, Fog, Kelp, Lagoon, Ocean, Orchid, Salmon, Sandcastle, Seaglass, Sunshine
DESCRIPTION	A solid chenille with an incredibly soft hand
END USE	Upholstery
WIDTH	58" wide
REPEAT	No Repeat
WEIGHT	13.79 ounces per linear yard
CONTENT	71.28% Polyester, 28.72% Seaqual Polyester
FLAME RESISTANCE	PASSES: NFPA 260, Cal 117-2013
FINISH	Alta™ DWR Performance Technology and Acrylic Backing
ABRASION	ASTM D4157 Wyzenbeek - 63,000 Double Rubs
COLORFASTNESS TO CROCKING	AATCC 8 - Wet: Class 4.5 / Dry: Class 4.5
COLORFASTNESS TO LIGHT	AATCC Method 16 (40 hours) - Class 4.5
PILLING	ASTM D3511 - Class 5
SEAM SLIPPAGE	ASTM D4034 - Warp: 92.5 lbs / Fill: 99.5 lbs
BREAKING STRENGTH	ASTM D5034 Warp: 140 lbs / Fill: 229 lbs
ENVIRONMENTAL	PFAS Free

COUNTRY OF ORIGIN USA

NORMAL CARE INSTRUCTIONS

Spot clean with upholstery shampoo, foam from a mild detergent, or mild cleaning solvent. Pretest a small, inconspicuous area before proceeding. Do not saturate. Pile fabrics may require brushing with a non-metallic, stiff-bristle brush to restore appearance. Hot water extraction or steam cleaning is not a recommended cleaning method. Cushion casings should not be removed and laundered or dry-cleaned. To prevent overall soiling, frequent vacuuming or light brushing with a non-metallic stiff-bristle brush to remove dust and grime is recommended. When cleaning a spill, blot immediately to remove spilled material. Clean spots or stains from the outside to the middle of affected area to prevent circling. Use a professional furniture cleaning service when an overall soiled condition has been reached.

All fabric subject to dye lot variations



ACT Registered Certification Marks

LebaTex recommends the end use of a product as specified on the spec sheet only. It is the customer's responsibility to determine code compliance if a product is to be used in a way other than its recommended end use. If a product is ultimately selected and installed in an application that it was not intended for, all liability falls to the customer.