

# TECHNICAL DATA SHEET



## Handi-Foam® Gun Foam Sealant



**Handi-Foam® Gun Foam Sealant** is a one-component insulating polyurethane foam (OCF) sealant specifically designed for use in small gaps, cracks, voids, and crevices. Using Handi-Foam Sealants to seal gaps and penetrations in the building envelope stops unwanted air infiltration. Less air infiltration into the building envelope improves comfort and results in less energy consumption. Handi-Foam Gun Foam Sealants utilize a (HC) propellant. Refer to the product storage and special handling section of this document for information regarding the use of flammable aerosol propellants. The product is for professional use only.

Handi-Foam Gun Foam Sealant is available in a 24oz or 29oz size and is designed to be dispensed through any Handi-Tool® dispensing unit.

### Application Areas

Apply Handi-Foam Gun Foam Sealant onto any clean surface to fill and seal around gaps, beneath base plates, mud sills, corner joints, T-joints, exterior cracks, around utility panels, pipes, duct penetrations, etc.

### Properties

The pre-pressurized portable OCF system, applied in a bead form, expands and cures slowly to a semi-rigid, closed cell foam upon reaction with moisture, such as ambient humidity.

Handi-Foam Gun Foam Sealant dries tack-free in approximately 5 minutes or less depending on moisture and temperature conditions. The foam fully cures within 24 hours. Expansion of 2-3 times the dispensed bead within the first hour should be expected. It is recommended to fill the cavity only 1/3 of the way full to allow for expansion. Handi-Foam Gun Foam Sealant will adhere to itself if more foam need be applied.

Handi-Foam Gun Foam Sealant adheres to almost all building materials with the exception of surfaces such as polyethylene, Teflon®, silicone, oils, greases, mold release agents, and similar materials.

Optimum chemical temperature is between 65-80°F (18-27°C), but may be applied in cold or hot ambient conditions, as long as the optimal chemical temperature range is maintained. Cured foam is dimensionally stable, and known to be resistant to temperatures ranging between -200°F to +240°F (-129°C to +115°C).

Handi-Foam Gun Foam Sealant is water resistant and will not harm electrical wire insulations, Romex, rubber, PVC, polyethylene or other plastic (i.e. PEX, CPVC). It is approved for use around wires, plumbing penetrations, etc. When cured, polyurethane foam is permanent, chemically inert, non-reactive and stable for an indefinite period of time. Cured foam should be protected against UV rays (i.e. sunlight) by painting or staining to prevent long term discoloration or degradation.

### Application/Use

After following instructions for set-up, the cans are ready to use. Attach the can to the dispensing unit (Handi-Tool), shake well, and begin dispensing. The dispensing units can be metered by pulling the dispensing unit trigger for the desired rate, or with the metering screw located in the back. Foam application can be interrupted when needed as outlined in the instructions and the dispensing unit will be ready for immediate re-use, as long as it remains attached to a pressurized container. An

empty gun foam container must be replaced with a new container.

Handi-Foam Gun Foam Sealant is especially useful for irregular voids and on non-linear cracks and crevices. Filling excessively large cavities can result in a prolonged curing process. Also, insufficient air or substrate moisture during cure may cause delayed expansion.

Remove fresh foam over spray with Handi-Cleaner® (P10083) or solvents such as acetone. Cured foam can only be removed mechanically.

Always refer to the local building codes before application of product.

### Personal Protective Equipment (PPE)

Use only in well ventilated areas. Wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure when using. Read all instructions and safety information prior to use of any product. Consult the product's (M)SDS (available at [www.fomo.com](http://www.fomo.com)).

### KEEP OUT OF REACH OF CHILDREN.

### Special Handling

The propellant is extremely flammable during dispensing and cure. Avoid breathing vapor or mist during dispensing. Provide sufficient cross-ventilation to remove any buildup of vapors. Keep away from heat, sparks and sources of ignition. Turn off all pilot lights. Vapors may cause flash fire if ignited. Contents are under pressure. Do not puncture, incinerate or store above 120°F (49°C). Do not place in hot water or near radiators, stoves, motor vehicles or other sources of heat. Cured urethane foam produced from these ingredients will support combustion and may present a fire hazard if exposed to a fire or excessive heat 240°F.

### Product Storage

Store upright in a dry area. Do not expose the product to open flame or temperatures above 120°F (49°C). Excessive heat can cause premature aging of components resulting in a shorter shelf life. Handi-Foam Gun Foam Sealant is reusable by following product instructions.

The unused product shelf life is 15 months when stored between 60-80°F (15.5-27°C). The expiration date can be found on the bottom of the can.

### Disposal

Do not incinerate containers. Relieve containers of any remaining foam and pressure before discarding. Always wear proper PPE during the disposal process and make sure discarded foam is fully cured. Dispose or recycle empty containers in accordance with all federal, state, provincial, and local regulations.

**Fomo Products, Inc.**  
A Member of the FLM Group of Companies  
management system registered to ISO 9001



2775 Barber Road PO Box 1078 Norton, Ohio 44203 USA  
p: 1 330.753.4585 1 800.321.5585 f: 1 330.753.5199  
[info@fomo.com](mailto:info@fomo.com) [www.fomo.com](http://www.fomo.com)

## Technical Data

<b>CORE DENSITY</b> ASTM D1622	1.00 lbs/ft <sup>3</sup> (16 kg/m <sup>3</sup> )
<b>K-FACTOR</b> ASTM C518-INITIAL	0.213 BTU·inch / ft <sup>2</sup> ·h·°F
<b>R-VALUE</b>	4.70 per inch
<b>AIR BARRIER PROPERTIES</b> ASTM E2178 @1.57 psf (75 Pa)	0.00028 cfm/ft <sup>2</sup> (0.0014 L/s/m <sup>2</sup> )
<b>TACK-FREE TIME</b>	Approx. 5 minutes
<b>FULLY CURES</b> 1" bead (at 70 °F 50% rh)	12-24 hours
<b>CUTTABLE</b> (1" Bead)	<1 hour
<b>COMPRESSION STRENGTH</b> ASTM D1621– PARALLEL	6.38 psi (43.9 kPa)
<b>Closed Cell Content</b>	67% Closed Cell
<b>Open Cell Content</b> ASTM D6226	33% Open Cell
<b>TENSILE STRENGTH</b> ASTM D1623	12 psi (83 kPa)
<b>FIRE RATING</b> ASTM E84 Caulking & Sealant Tested at 3/4" bead thickness	Flame Spread Index = 25 Smoke Developed =50
<b>FIRE RATING</b> CAN/ULC S102 Caulking & Sealant Tested at 3/4" bead thickness	Flame Spread Index = 15 Smoke Developed =25

## Approvals / Standards

Handi-Foam One-Component Gun Foam Sealant conforms to the following Classifications, Codes and Standards:

VOC Content: 16% or 165 g/L (Calculated Value)

NFPA 30B Classification: Level 2 Aerosol

UL Classified - File # R13919 Caulking and Sealants  
UL 723/ASTM E-84 (12.5%)  
Flame Spread 25 Smoke Developed 50

ULC Classified - File # R13919 Caulking and Sealants  
CAN/ULC S102 (12.5%)  
Flame Spread 15 Smoke Developed 25

GREENGUARD Certifications

CCMC #13626-L

Made in Norton, Ohio

## Theoretical Yield\*

	1/4" (6.3 mm)	3/8" (9.5 mm)	1/2" (12.7 mm)	VOLUME
24oz (680g) Gun Foam P30115	4403 ft (1342 m)	1957 ft (596 m)	1101 ft (336 m)	1.50 ft <sup>3</sup> ( 42 L)
29oz (820g) Gun Foam P30290	5313 ft (1619 m)	2361 ft (720 m)	1328 ft (405 m)	1.81 ft <sup>3</sup> ( 51 L)

\*Yields are based on theoretical calculations, for comparison purposes, and will vary depending on ambient conditions and particular application.

**Always read all operating, application and safety instructions before using any products from Fomo Products, Inc.** Use in conformance with all local, state and federal regulations and safety requirements. Failure to strictly adhere to any recommended procedures and reasonable safety precautions shall release Fomo Products of all liability with respect to the materials or the use thereof. For additional information and location of your nearest distributor, call Fomo Products, Inc. 1 330.753.4585 or 1 800.321.5585.

**NOTE:** Physical properties shown are typical and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions and may vary upon use, temperature and ambient conditions. Right to change physical properties as a result of technical progress is reserved. This information supersedes all previously published data. Yields shown are based on theoretical calculations and will vary depending on ambient conditions and particular application. Read all product directions and safety information before use. Consult local building codes for specific requirements regarding the use of cellular plastics or urethane products in construction.

**WARNINGS:** Follow safety precautions and wear protective equipment as recommended. Consult Safety Data Sheet (SDS) at [www.fomo.com](http://www.fomo.com) for specific information. Use only in a well ventilated area or with certified respiratory protection. NIOSH approved positive pressure supplied air respirator is recommended if exposure guidelines may be exceeded. Contents may be very sticky and irritating to skin and eyes, therefore wear safety glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure when operating. If liquid chemical comes in contact with skin, first wipe thoroughly with dry cloth, then rinse affected area with water. Wash with soap and water afterwards, and apply hand lotion if desired. If liquid comes in contact with eyes, immediately flush with large volume of clean water for at least 15 minutes and get medical help at once. If liquid is swallowed, get immediate medical attention. Products manufactured or produced from these chemicals are organic and, therefore, combustible. Each user of any product should carefully determine whether there is a potential fire hazard associated with such product in a specific usage. **KEEP OUT OF REACH OF CHILDREN.**

**LIMITED WARRANTY:** The Manufacturer warrants only that the product shall meet its specifications: THIS WARRANTY IS IN LIEU OF ALL WRITTEN OR UNWRITTEN, EXPRESSED OR IMPLIED WARRANTIES AND THE MANUFACTURER EXPRESSLY DISCLAIMS ANY WARRANTY OF MERCHANTABILITY, OR FITNESS FOR A PARTICULAR PURPOSE. The buyer assumes all risks whatsoever as to the use of the material. Buyer's exclusive remedy as to any breach of warranty, negligence or other claim shall be limited to the replacement of the material. Failure to strictly adhere to any recommended procedures shall release The Manufacturer of all liability with respect to the materials or the use thereof. User of this product must determine suitability for any particular purpose, including, but not limited to, structural requirements, performance specifications and application requirements prior to installation and after product is applied.



### Handi-Foam Gun Foam Sealant

Fomo Products, Inc. p: 1 330.753.4585, 1 800.321.5585 f: 1 330.753.5199  
info@fomo.com www.fomo.com

