



REPORT OF ANALYSIS

Client : MULTISTEPS PTY LTD UNIT 20 SLOUGH BUSINESS PARK (OFF RACHAEL CLOSE) SILVERWATER NSW 2128	Job No. : MULT16/180105 Quote No. : QT-02094 Order No. : Date Sampled : Date Received : 5-JAN-2018 Sampled By : CLIENT
Attention : ALEX TSE Project Name : Your Client Services Manager : Tony Lattari	Phone : 02 9449 0196

Lab Reg No.	Sample Ref	Sample Description
V18/000695	4	Soaker pad material

Lab Reg No.	Sample Reference	Units	V18/000695	4	Method
Simulant 1					
Barium (1)	mg/kg	< 1			VL413
Cobalt (1)	mg/kg	< 0.05			VL413
Copper (1)	mg/kg	< 5			VL413
Iron (1)	mg/kg	< 48			VL413
Lithium (1)	mg/kg	< 0.6			VL413
Manganese (1)	mg/kg	< 0.6			VL413
Zinc (1)	mg/kg	< 25			VL413
Simulant 2					
Barium (2)	mg/kg	< 1			VL413
Cobalt (2)	mg/kg	< 0.05			VL413
Copper (2)	mg/kg	< 5			VL413
Iron (2)	mg/kg	< 48			VL413
Lithium (2)	mg/kg	< 0.6			VL413
Manganese (2)	mg/kg	< 0.6			VL413
Zinc (2)	mg/kg	< 25			VL413

V18/000695

These results indicate that the material, as supplied, does comply with AS2070-1999 with respect to the stated testing procedures.

Nunzio Limongiello, Analyst
Inorganics - Vic

5-FEB-2018

REPORT OF ANALYSIS

Page: 2 of 2
Report No. RN1185143

Lab Reg No.		V18/000695				
Sample Reference	Units	4				Method
Simulant 1						
Simulant Type (1)		3% Acetic A				VL413
Simulation Time (1)		10 days				VL413
Simulation Temp (1)		20 degrees				VL413
Gravimetric (Area) (1)	mg/dm ²	< 10				VL413
Total Phthalates (1)	%w/w	< 0.1				VL413
Total SVOC (1)	mg/L	Not Detect				VL413
Simulant 2						
Simulant Type (2)		10% Ethanol				VL413
Simulation Time (2)		10 days				VL413
Simulation Temp (2)		20 degrees				VL413
Gravimetric (Area) (2)	mg/dm ²	< 10				VL413
Total Phthalates (2)	%w/w	< 0.1				VL413
Total SVOC (2)	mg/L	Not Detect				VL413
Compliance to AS2070-1999 10/2011						
Result		Comply				VL413

V18/000695

Devika Kodituwakku

Devika Kodituwakku, Analyst
Inorganics - Vic

5-FEB-2018

Results relate only to the sample(s) tested.
This Report shall not be reproduced except in full.