

Renaissance Lime Putty

Guide of suggested mix ratios for stucco and plasterwork expressed in parts by volume.

Mixes may vary depending on specific aggregate size/shape/composition and purpose of application.

Repointing of brick and stone: Large joints = Scratch coat mix - Small joints (less then 3/16") = Finish coat mix.

Bedding mortar for brick and stone: Scratch coat mix.

Mortar thickness should ideally be kept between 1.5 to 3 times the size of the largest aggregate particle per coat.

Renaissance Lime Putty	Lime putty	NHL-5	Marble/Limestone aggregate	Marble/Limestone aggregate	Coarse siliceous sand	Fine siliceous sand	Cocciopesto pozzolana	Cocciopesto pozzolana
			0 to 3 - 4 mm.	0 to 1.5-2 mm.	0 to 3 - 4 mm.	0 to 1.5-2 mm.	0 to 3 - 4 mm.	0 to 1.5-2 mm.
Scratch coat	1	1	6					
Scratch coat	1	1			5			
Scratch coat	1	1	4				1-1/2	
Scratch coat	1		3					
Scratch coat	1				2-1/2 to 3			
Brown coat	1	1	5					
Brown coat	1	1			4			
Brown coat	1						2	
Brown coat	1		2-3/4					
Brown coat	1				2-1/2			
Finish coat	1	1/4		2 -1/2				
Finish coat	1	1/4				2		
Finish coat	1							1-1/2
Finish coat	1			2				
Finish coat	1					1-3/4 to 2		