



0326 Leak Stopper® Rubber Flexx Sealant White

- Stops Leaks
- Seals & Protects
- Easy Spray Application
- Use on: Roofs, Chimneys, Skylights, Gutters, Pipes & more

A white colored, spray applied coating that provides a flexible seal against the elements. The coating is crack resistant and won't peel. Economical, quick, and easy to use. Also helps protects against rust and corrosion.

DIRECTIONS

- Surface must be clean and dry before painting. Protect surrounding areas from spray mist. For best results, use when can is between 50°F and 90°F (10°C and 32°C).
- 2. Shake can at least one minute after rattle is heard and occasionally during use.
- 3. Spray surface with steady even strokes at a distance of 2 to 10 inches (5 to 5cm). Multiple coats may be applied, allowing 20 to 30 minutes between coats.
- 4. If clogging develops, turn sprayhead 1/4 turn or remove and clean sprayhead slot. DO NOT stick pin or other objects into can opening. With can and sprayhead pointed away from you, reinsert sprayhead with a gentle twisting motion.
- 5. To clear sprayhead for future use, turn can upside down and spray for 3 seconds. Completely empty cans may be recycled or disposed of with regular trash. Dispose of partially empty cans responsibly. DO NOT incinerate or compact.

PRECAUTIONS: For exterior use only. Do not use in drinking water or food systems. Do not use on EPDM, Hypalon or PVC surfaces. Do not use on single ply or synthetic roofs. If there is any question regarding compatibility, test a small section first. Product will dry to touch in 10 minutes. Full cure or before recoating may take up to 4 hours. For longest life, store in controlled environment, 50°F to 85°F.

CALIF. PROP. 65 • WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects or other reproductive harm. Use proper protection and adequate ventilation, when using product. Flat Paint Products Do Not Exceed 60% VOC OR 1.20 MIR

DANGER! EXTREMELY FLAMMABLE LIQUID AND VAPOR. VAPORS MAY CAUSE FLASH FIRE. CONTENTS UNDER PRESSURE. VAPOR HARMFUL.

VAPOR HARMFUL. MAY AFFECT THE BRAIN OR NERVOUS SYSTEM CAUSING DIZZINESS, HEADACHE OR NAUSEA. CAUSES EYE, SKIN, NOSE AND THROAT IRRITATION. KEEP OUT OF REACH OF CHILDREN. Do not puncture or incinerate (burn) container. Exposure to heat or prolonged exposure to sun may cause bursting. Do not expose to heat or store at temperatures above 120°F (49°C).

NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.

Vapors may ignite explosively. Keep away from heat, sparks and flame. Do not smoke. Extinguish all flames and pilot lights, and turn off stoves, heaters, electric motors and other sources of ignition during use and until all vapors are gone. Prevent build-up of vapors by opening windows and doors to achieve cross-ventilation.

Use only with adequate ventilation. Do not breathe dust, vapors or spray mist. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air or wear respiratory protection (NIOSH/MSHA approved) or leave the area. Avoid contact with eyes, skin and clothing.

First Aid: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water.

Contains: Calcium Carbonate 1317-65-3, VM&P Naphtha 64742-89-8, Propane 74-98-6, Toluol 108-88-3, Heptane 142-82-5, Acetone 67-64-1, NButane 106-97-8, Titanium Dioxide 13463-67-7, PM Acetate 108-65-6, Xylene 1330-20-7, Mineral Spirits 64742-47-8. OTHER INGREDIENTS: "Contents Partially Unknown".

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS	
Flammability	Extremely Flammable
Flash point	-4° F
Specific Gravity	0.82
Solids Content	31%
VOC content	Less than 59%, cannot exceed 60%
MIR value	Less than 1.15, cannot exceed 1.20
HAPs content	Less than 4%
Storage Temperature	40°-90°F
Application Temperature	50°-100°F
Durability	Excellent
Abrasion Resistance	Very Good
Heat Resistance	Up to 250° F
Gasoline Resistance	No
Thermoplastic	Elastomer
Shelf life	Guaranteed for 2 years
Cure Time*: To touch Cure Time*: To handle	10 minutes 4-6 hours
* At 72° F, 50% humidity, 1.5 mil thickness. Curing/Recoat time is extended with multiple coats and excessively thick coats.	
Approx. Shipping Weights: (Note: All approx. weights include container.)	
15 oz. Aerosol can	1.4 lbs.
(12) 15 oz. containers/case	18 lbs.
Shipping Classification	Consumer Commodity ORM-D UN 1950
Hazard Class	2.1