## **How to Apply Elastomeric Roof Coatings**



STEP 1: PREPARE THE SURFACE

- Clear roof surface of loose debris including dirt, gravel, sticks, etc. using a push broom or blower
- Clean with Gardner Power Kleen<sup>™</sup> or a pressure washer.
- Patch and repair cracks, blisters and other problem areas using Black Jack White Acrylic Roof Patch, following label directions. Reinforce repairs with Sta-Kool Stress Block™ reinforcement fabric.

## RECOMMENDED SURFACES

- Metal
- Urethane/polystyrene foam
- Concrete roofs
- · Aged rolled roofing and aluminum coatings
- Flat and barrel cement tile



STEP 2: APPLY ELASTOMERIC COATING

On a clear, warm, sunny day, roll, brush or spray Black Jack®, Gardner™ or STA-KOOL® White Elastomeric Roof Coating to a dry roof surface. Follow all label directions.

## RECOMMENDED APPLICATORS

Roof brush, 3/4" nap roller, or airless spray in 10"-12" pattern, 2000 psi, .021 to .025 spray tip

## COVERAGE RATES: TWO COATS RECOMMENDED

Metal 80 to 100 sq ft. per a gallon Foam 50 to 75 sq. ft. per a gallon Concrete tile 50 to 75 sq. ft. per a gallon