



## **Installation Guide: Pre-Sealed Saltillo**

Elon® **ALWAYS** recommends that all installations be done in accordance with local building codes and adhere to Tile Council of North America specifications.

### **Preparation**

*Prior to installation of Pre-Sealed Saltillo:*

- Pre-sealed Saltillo cartons should all be opened and inspected.
  - Imperfections such as hairline chips, cracks, bumps, shade, and size variations are inherent to handmade pre-sealed Saltillo and are not considered defects. Every piece will be different from any other piece in the installation.
- All cartons should be opened, and material should be separated to allow the installer to layout all pieces and blend them together to give the final installation a uniform color blend, known as "Dry Laid."
- On large jobs, always blend material from multiple pallets when Dry Laying pre-sealed Saltillo.
- When installing pre-sealed handmade Saltillo, always allow for extreme size variations between pieces. When laying out for the installation, select a joint width between 3/8" to 3/4" based on the size variations of the material being installed.
- Lime or salt pops are caused when minerals found in the clay expand and cause slight pits to develop in the surface of the Saltillo.
  - Lime or salt pops will occur both during and after the installation and are not defects but are characteristics of the material that will add to the Old-World Charm of the installation.

### **Installation**

*When installing Pre-Sealed Saltillo:*

- Many setting material manufacturers recommend using latex modified thinset for Pre-sealed Saltillo tile on both walls and floors rather than mastics, due to the extreme porosity of the Saltillo bisque or body.
  - Always follow the manufacturer's Instructions and limitations.
- When used in showers or tubs, pre-sealed Saltillo should never be set with the bottom course extending into the shower base or tight to tub lip. Always leave a minimum gap of 1/4" above and perpendicular to the floor or lip of the tub or shower base and use a waterproof flexible sealant where they meet per TCNA specification B412-23.
  - This will prevent water from wicking up the body and causing discoloration and water lines to be seen.

### **Grouting**

*Grouting Pre-Sealed Saltillo:*

- When grouting pre-sealed Saltillo, always do a test sample first.
- Grout joint widths should range from a minimum 3/8" width to a maximum of 3/4" for this type of grout.
- Sanded grout for handmade pre-sealed Saltillo will be a MUST.

## Sealing

Contact professional floor care for Re-Sealing of Saltillo products.

- Always do a test area first.

## Common Problems

*Common problems in Pre-Sealed Saltillo:*

- Lime or salt pops WILL occur both during and after the installation and are not defects but are characteristics of the material that will add to the charm and character of the installation.
  - Simply apply an additional sealer to the area, and it will blend in with the rest of the installation.
  - If a void occurs in the surface, it can be filled with grout prior to resealing the area.
- Many times, irregular joints and lippage or uneven surface height are results of Saltillo installed with too tight of a grout joint.
  - 3/8" to 3/4" grout joints will allow imperfections in the Saltillo to be blended, creating a uniform installation.
- Always inspect material prior to installation.

### **Installation is Acceptance**

This Tile Installation Guide provided by Elon® Tile & Stone is intended solely for educational purposes. Users must understand that the information herein is not a substitute for professional advice. Elon® Tile & Stone does not assume any responsibility for the accuracy, completeness, or outcomes resulting from the application of the provided guidelines. Users utilize this guide at their own risk. It is imperative to consult with qualified professionals and adhere to specific product guidelines for optimal results. Elon® Tile & Stone, its employees, and affiliates expressly disclaim any liability for direct, indirect, or consequential damages arising from the use of this guide.