




Performance Data Sheet
Lithium Cobalt Oxide - Power



| Capacity of LCOP at different rates mAh | | |
|---|--------|--------|
| Rate | Cell 1 | Cell 2 |
| 1C | 1485 | 1454 |
| 10C | 1502 | 1451 |
| 20C | 1499 | 1447 |
| 25C | 1493 | 1440 |
| 30C | 1491 | 1434 |
| 35C | 1485 | 1425 |
| 40C | 1465 | 1406 |

| Energy Power Density and Specific Energy and Power at 1C rate for LCOP | | | |
|--|--------|--------|---------------------|
| Description | Cell 1 | Cell 2 | Unit |
| Energy Density | 41.6 | 40.7 | mAh/g |
| Power Density | 158.6 | 155.2 | mWh/g |
| Specific Energy | 0.094 | 0.092 | mAh/mm ³ |
| Specific Power | 0.360 | 0.352 | mwh/mm ³ |

www.electrodesandmore.com

Battery Consulting, 4020 Christopher Way, Plano TX 75024
Phone: (877)394-3941 Fax: (208)955-4890
drmumu@electrodesandmore.com

