



SPECTRALOCK® 1 Pre-mixed Grout†

DS-36589.1-1019

**Globally Proven
Construction Solutions**



- High fashion when combined with Part D - Dazzle component
- Can be used for grout joints from 1/16-3/8"
- Finished product equivalent to SPECTRALOCK Pro Premium Epoxy Grout

* Stain proof (residential installations only) to common household cleaners, liquids and other goods. Clean all spills immediately.

Packaging

Unit Size	Weight
1 GAL (3.8L)	14.2 LB (6.4kg)

Pallet Quantity

- 1 GAL – 80 Units per pallet

Approximate Coverage (1 GAL Pail)

US/Metric Impériale/métrique EE. UU./Métrico	Joint widths/ Largeurs des joints/ Ancho de las juntas			
	1/16" (1.5 mm)	1/8" (3 mm)	1/4" (6 mm)	3/8" (9 mm)
Tile dimension Dimension des carre aux Tamaño del azulejo				
1" x 1" x 1/4" (25 x 25 x 6 mm)	53 ft ² (5.4 m ²)	27 ft ² (2.8 m ²)	15 ft ² (1.5 m ²)	11 ft ² (1.1 m ²)
2" x 2" x 1/4" (50 x 50 x 6 mm)	104 ft ² (10.7 m ²)	53 ft ² (5.4 m ²)	27 ft ² (2.8 m ²)	19 ft ² (1.9 m ²)
3" x 6" x 5/16" (76 x 152 x 8 mm)	168 ft ² (16.4 m ²)	86 ft ² (8.4 m ²)	45 ft ² (4.5 m ²)	31 ft ² (3.1 m ²)
4 1/4" x 4 1/4" x 5/16" (106 x 106 x 8 mm)	176 ft ² (18 m ²)	89 ft ² (9 m ²)	45 ft ² (4.5 m ²)	30 ft ² (3.0 m ²)
4" x 24" x 3/8" (102 x 610 x 9 mm)	238 ft ² (24.9 m ²)	121 ft ² (12.6 m ²)	62 ft ² (6.5 m ²)	43 ft ² (4.5 m ²)
6" x 24" x 3/8" (152 x 610 x 9 mm)	332 ft ² (34.5 m ²)	168 ft ² (17.4 m ²)	86 ft ² (8.9 m ²)	58 ft ² (6.0 m ²)
12" x 24" x 3/8" (305 x 610 x 9 mm)	551 ft ² (57.3 m ²)	277 ft ² (28.8 m ²)	140 ft ² (14.6 m ²)	95 ft ² (9.8 m ²)
24" x 24" x 3/8" (610 x 610 x 9 mm)	822 ft ² (85.8 m ²)	412 ft ² (43.1 m ²)	206 ft ² (21.7 m ²)	138 ft ² (14.6 m ²)
12" x 36" x 3/8" (305 x 914 x 9 mm)	619 ft ² (64.5 m ²)	311 ft ² (32.4 m ²)	158 ft ² (16.4 m ²)	106 ft ² (11 m ²)

1. PRODUCT NAME

SPECTRALOCK® 1 Premixed Grout†

2. MANUFACTURER

LATICRETE International, Inc.
1 LATICRETE Park North
Bethany, CT 06524-3423 USA

Telephone: +1.203.393.0010, ext. 235
Toll Free: 1.800.243.4788, ext. 235
Fax: +1.203.393.1684
Website: www.laticrete.com

3. PRODUCT DESCRIPTION

SPECTRALOCK 1 is a patent pending, pre-mixed, stain proof grout with epoxy performance offering superior strength, fastest cure time, and the ability to be submerged. While meeting the standards of ANSI A118.3.

Uses

- Ceramic tile, glass tile and stone
- Residential and commercial
- Interior and exterior
- Floors and walls
- Ideal for re-grouting applications
- Swimming pools, fountains and other wet area applications

Advantages

- Has the same performance as an Epoxy (ANSI A118.3) product without the epoxy resins
- 10 times stronger than traditional premixed grout
- Stainproof*
- Non-sag formula for walls and floors
- Uniform color—no blotchiness or shading
- Never needs sealing
- Easy to maintain, cleanable to the original color
- Tough, durable, and crack resistant

Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for the time listed below if stored at temperatures greater than 32°F (0°C) and less than 95°F (35°C).

Two (2) years

Limitations

- Not for use in areas subjected to harsh chemicals, or areas exposed to aggressive cleaning regimens (e.g. steam cleaning). Not for use on floor and base areas in veterinary clinics, kennels, or in applications exposed to high concentrations of food and mineral acids or areas exposed to high temperatures. For these areas LATICRETE recommends using grout that meets ANSI A118.5 such as SPECTRALOCK 2000 IG.
- Premixed grouts for ceramic tile and stone are not a replacement for a waterproofing membrane. When a waterproofing membrane is required, use a LATICRETE® Waterproofing Membrane (see Section 10 FILING SYSTEMS).
- SPECTRALOCK 1 Premixed Grout† should not be used on floors and bases in the food preparation or cleaning area of commercial kitchens. We recommend the use of SPECTRALOCK 2000IG for these types of installations.
- Stainproof to common household cleaners, liquids and other goods. Clean all spills immediately. Stainproof in residential installations only.

Cautions

Consult SDS for more safety information.

- DO NOT add water or any other material to the mixture, or re-temper with water. This will have an adverse effect on the product and void all warranties.
- Protect finished work from traffic until fully cured.
- SPECTRALOCK 1 Premixed Grout† could irritate eyes and skin. Avoid contact with eyes and/or prolonged contact with skin.
- DO NOT ingest internally. See SDS for more information.
- Keep out of reach of children.
- Protect from freezing.
- SPECTRALOCK Part D DAZZLE™ (Glow) not for use in submerged installations.
- Maximum stain protection is achieved in 7 days at 70°F (21°C). Protect from exposure to acids (such as mustard, salad dressing, etc.) and strong cleaners during this period. Protect grout from dirt, construction debris, and contamination for 7 days @ 70°F (21°C).
- Some soft polished marble or delicate glazed or glass tile might be scratched by SPECTRALOCK 1 Premixed Grout† during installation. Apply a small test area to determine results before grouting entire installation.
- In steam rooms or submerged applications, allow SPECTRALOCK 1 Premixed Grout† to cure for 10 days at 70°F (21°C) days before use of area and filing with water. See TDS 192 for more information on these applications.
- SPECTRALOCK 1 Premixed Grout† could affect the color of white or porous stones (such as White Carrara, Thassos White, Royal Danby etc.). Apply a small test area to determine results before grouting entire installation.
- Test stones for compatibility with water and cleaning additive mixture.
- Conduct a test area to determine compatibility with metal or steel tile.

4. TECHNICAL DATA

VOC/LEED Product Information

This product has been certified for Low Chemical Emissions (ULCOM/GG UL2818) under the UL GREENGUARD Certification Program For Chemical Emissions For Building Materials, Finishes and Furnishings (UL 2818 Standard) by UL Environment.

Total VOC Content form is 0.00026 lb/gal (0.031 g/l).

Applicable Standard

None (but meets ANSI A118.3 Criteria)

Physical Properties

Test/Test Method	Description	Results
ANSI A118.3 E5.1	Water Cleanability	Pass
ANSI A118.3 E5.2	Initial Set Service Strength	> 2 hours < 8 hours
ANSI A118.3 E5.4	Vertical Joint Sag	Pass
ANSI A118.3 E5.5	Quarry/Quarry Bond Strength	644 psi - 918 psi (4 – 6.3 MPa) 28days
ANSI A118.3 E5.6	Compressive Strength	3242 - 3600 psi (22.3 – 25 MPa) 14 Days
ANSI A118.3 E5.7	Tensile Strength	800 - 900 psi (5.5 – 6.2 MPa) 14 Days
ANSI A118.3 E5.8	Thermal Shock	561 psi (4 MPa)



Chemical Resistance*** Chart

Chemical Name	Splash Exposure (30 min)	Intermittent Exposure (24 hours)	Continuous Exposure (7 days)
20% Sulfuric acid	R	R	R
5% Lactic acid	R	R	NR
50% Tannic acid	R	R	NR
50% Tartaric acid	R	R	R
10% Oxalic acid	R	R	NR
5% Acetic acid	R	R	NR
5% Benzoic acid	R	R	NR
3% Formic acid	R	R	NR
5% Citric acid	R	R	NR
1% potassium Permanganate	R*	R*	NR
5% Sodium Hyperchlorite	R	R	NR
45% KOH	R	R	NR
Distilled water	R	R	NR
Mineral Water	R	R	NR
Sea Water	R	R	NR
Methanol	R	R	NR
10% Ethanol	R	R	NR
96% Ethanol	R	R	NR
Isopropanol (Windex)	R	NR	NR
Mek	R	NR	NR
Methylene chloride	R	R	NR
Toluene	NR	NR	NR
Xylene	NR	NR	NR

* Material will stain due to exposure to these items.

R=Recommended NR=Not Recommended. Chemical Resistance determined in accordance with ASTM C267-1982.

NOTES TO SPECIFIER: Use the constant exposure recommendations for intermittent exposure to reagents at temperatures above 90°F (32°C).

Working Properties

Density—14.2 lbs/gal (1.7 g/cc)

Test Standard	Test Description	Temperature		
		50°F (4°C)	70° (21°C)	90°F (35°C)
LIL-AS-01-110904	Tack Free Time	4 hrs.	1 - 2 hrs.	45 min.
LIL-AS-01-110904	Ready for Light Foot Traffic	9 hrs.	6 hrs.	4 hrs.
LIL-AS-01-110904	Ready for Heavy Foot Traffic	48 hrs.	24 hrs.	10 hrs.
LIL-AS-02-110904	Dirt, Stain Resistance, Food Spills, Household Cleaners	21 days	14 days	10 days
LIL-AS-03-110904	Full Cure	28 days	28 days	14 days

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions as well as size of the grout joint installed.

5. INSTALLATION

Surface Preparation

See Data Sheet 736589.5, How To Install SPECTRALOCK® 1 Pre-mixed Grout†, for detailed installation instructions. This document is available online at www.laticrete.com.

Please note that working time is affected by many variables including surface and room temperatures. Warmer climates, for example, will shorten curing & working time, while colder conditions will extend the cure time.

Do not add water or any other materials to the grout mixture. This will have an adverse effect on the product and void all warranties.

Prior to grouting, apply SPECTRALOCK 1 to a small area to ensure the product will not stain.

With any mixed media type tile installation, such as stone, metal and plastic type tiles, we recommend testing a small area before installation and start to clean the grout sooner for best results.

Clean-up is critical. Prepare for the initial and final washes by having pails of clean water ready for the clean-up process.

Application

NOTE: After surfaces are cleaned, allow to dry thoroughly before grouting.

- Spread grout using a sharp edged, firm rubber grout float. Work the grout diagonally across the joints, packing them full.
- “Cut” excess grout off the tile surface using the edge of the float held at a 90° angle like a squeegee, stroking diagonally to avoid pulling grout out of filled joints.

Cleaning

NOTE: Have clean water, new clean sponge, nylon scrub pad (doodlebug) and clean microfiber towel ready.

- Once grout has been spread, wait approximately 5-10 minutes before cleaning (or within an “arms-length” of what has been spread). Wait slightly longer at colder temperatures.

- Submerge clean sponge into water and wring until the sponge is moist but not dripping with water. Putting too much water on the grout joints could affect the cure time and appearance of grout joints.
- Change water every 50 ft² (4.6 m²).
- Wipe grout joints and tile surface in a light circular motion, loosening grout residue while keeping the joints smooth and full.
- Drag a clean sponge diagonally over the scrubbed surfaces to remove any remaining grout residue.
- For best results, we recommend to rinse sponge after every final pass; use each side of sponge only once between rinsing.
- Check work as you clean. If necessary, repair any low spots with additional grout.

WALL APPLICATIONS

Instead of a sponge, the use of a damp, well wrung, folded terry cloth towel can be helpful to remove excess grout while smoothing joints less than 1/8” (3 mm) on walls. Use light pressure when using folded terry cloth towel.

FINAL INSPECTION AND CLEANING

- Begin final cleaning when grout joints are hard to the touch, depending upon the size of the grout joint and the ambient temperature. Smaller grout joints (1/16” (1.6mm) or 1/8” (3.2mm)) would take less time to start to clean, approx. 45 min. For larger grout joints (3/8” (9.5 mm)) we recommend waiting about 1 hour to ensure the grout joints are hard and cannot be disturbed with the second cleaning.
- Use only clean water and simply dunk the nylon scrub pad (doodlebug) in the water and let all the water pour out – it should be nearly dry and then start to break up the grout haze left from the initial wash on the surface of the tiles.
- Rinse scrub pad frequently, letting all water escape before continuing to clean.
- Then, use a clean cloth to the scrubbed surfaces to remove any residue.
- Allow cleaned areas to dry and inspect tile/stone surface.
- If haze remains on the tiles the following day, it can be buffed off the using a nylon scrub pad (doodlebug).
- Make certain to check tile surface with adequate lighting after the tile surface is dry.
- Conduct a test area to verify results on polished stones.
- Rinse with clean water and allow surface to dry. Inspect grout surface and repair as required with fresh grout.
- For ANY area that will later receive intermittent water exposure, allow area to cure 24 hours.
- Protect finished surface from traffic for at least 12 hours at 70°F (21°C).
- Do not expose grout to acid cleaners for 7 days.
- Allow grout to cure for 10 days at 70°F (21°C) prior to use in submerged applications or steam rooms.

See LATICRETE Technical Data Sheet 192 for more information on grouting of ceramic tile in submerged installations.

For use with our SPECTRALOCK® Dazzle™ Please follow these instructions to use with any color in the SPECTRALOCK 1 Pre-mixed Grout:

- Obtain a 1 gal (3.8 L) bucket of SPECTRALOCK 1 Pre-mixed Grout and an empty 1 gal (3.8 L) bucket.
- With a margin trowel – take approx. 1/2 of the material within the SPECTRALOCK 1 Pre-mixed Grout bucket and place within the empty bucket.
- Then in the center of each bucket create a small hole with a margin trowel.
- Open the Dazzle (any color) and proceed to place 1/2 of the jar within each bucket inside the small holes in the center of each bucket.
- Next, take a good scoop of SPECTRALOCK 1 Pre-mixed Grout and cover the Dazzle in the hole very slowly and gently (this helps to mitigate the Dazzle from dispersing in the air and out of the bucket).
- Then proceed to mix by hand (It is not recommended using any drills to mix the SPECTRALOCK 1 Pre-mixed Grout since that would help to incorporate more air in the mixture – potentially speed up the cure/setting process).
- Thoroughly mix the dazzle and disperse throughout the bucket.
- Once each bucket has been mixed extensively and the Dazzle seems to be dispersed evenly within each bucket – then add the other 1/2 gal (1.9 L) back into the original bucket.

Now you are ready to grout or reseal the original bucket to keep the SPECTRALOCK 1 from skimming over & curing.

6. AVAILABILITY AND COST

Availability

LATICRETE and LATAPOXY® materials are available worldwide.

For Distributor Information, Call:

Toll Free: 1.800.243.4788

Telephone: +1.203.393.0010

For on-line distributor information, visit LATICRETE at

www.laticrete.com

Cost

Contact a LATICRETE Distributor in your area.

7. WARRANTY

See 10. FILING SYSTEM

DS230.13: LATICRETE Product Warranty

A component of:

DS025.0: LATICRETE 25 Year System Warranty (United States and Canada)

DS230.99: LATICRETE Lifetime System Warranty (United States and Canada)

8. MAINTENANCE

Protect surfaces from common stains by using a STONETECH sealer such as STONETECH BulletProof® Sealer. Routine maintenance should follow with STONETECH Revitalizer® Cleaner and Protector or a neutral pH cleaner such as STONETECH Stone & Tile Cleaners. For tough or difficult to remove soil use STONETECH KlenzAll™ Cleaner, a nylon scrubbing pad or a long handled stiff bristle brush. For additional information, please refer to the Grout Guide, TDS 400 and TDS 113 Cement Grout Care & Maintenance for more information.

9. TECHNICAL SERVICES

Technical Assistance

Information is available by calling the LATICRETE Technical Service Hotline:

Toll Free: 1.800.243.4788, ext. 1235

Telephone: +1.203.393.0010, ext. 1235

Fax: +1.203.393.1948

Technical and Safety Literature

To acquire technical and safety literature, please visit our website at www.laticrete.com.

10. FILING SYSTEM

Additional product information is available on our website at www.laticrete.com. The following is a list of related documents:

DS 230.13: LATICRETE Product Warranty

DS 025.0: LATICRETE 25 Year System Warranty (United States and Canada)

DS 230.99: LATICRETE Lifetime System Warranty (United States and Canada)

DS 236.0: 9235 Waterproofing Membrane

DS 634.0: SPECTRALOCK 2000 IG

DS 663.0: HYDRO BAN®

TDS 400: LATICRETE Grout Guide

TDS 192: Installation of Ceramic Tile In Swimming Pools

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

©2013 LATICRETE International, Inc.

All trademarks shown are the intellectual properties of their respective owners.