

# NATIONAL POOL FINISHES



- Upgrades KOOL DECK™ Surfaces
- Painted or Unpainted Concrete Surfaces
- Cleans Up With Soap & Water
- Cures Quickly
- No Solvent Fumes
- Back In Service Quickly
- Excellent Color Retention

## DECK KOTE™

### The New Science of Deck Coatings™

### ACRYLIC WATER-BASED DECK PAINT

#### DECK KOTE™ - Acrylic Water-Based Deck Paint

A Premium one-part acrylic water-based deck coating designed as an effective weapon against UV rays and weathering in a coating that is easy to apply and clean up. Longest lasting protection against fade on painted or unpainted concrete surfaces. Dries quickly, durable, and resists fading, chemicals, and abrasion. Rejuvenates ELITE and other textured deck surfaces. For non-skid surfaces, add sand or pumice stone as desired. Cleans up with soap and water. Designed for maximum protection against algae, UV rays and chlorine.

**SUGGESTED USES:** Painted or unpainted concrete surfaces.

**COLORS:** Available in 6601 Sand Buff, 6602 Adobe Buff, 6603 Aztec Gold, 6604 Aqua, 6605 Birch Gray, 6607 Coral Peach, 6609 New England Blue, 6610 White, 6011 Sandstone Brown, 6612 Canyon Brown

**FINISH:** Flat. For a non-skid finish, add pumice stone, sand or marble dust to paint as needed to achieve desired appearance.

**VEHICLE TYPE:** Acrylic Resin

**SOLVENT TYPE:** Water, Butyl Cellosolve, Diacetone Alcohol, Ethylene Glycol

**VOC:** 1.6 lbs. / gal (190 grams / liter)

**FLASH POINT:** Non Flammable

**SOLIDS BY WEIGHT:** 50%

**WEIGHT PER GALLON:** 11 lbs. per gallon (varies by color)

**RECOMMENDED DRY FILM:** 4.0 mils

**COVERAGE:** Theoretical coverage at two mils dry is 350 square feet per gallon, and recommended thickness of 4 mils dry would require 2 full coats. Material losses during mixing and application will vary and must be taken into consideration. Expect 50% less coverage on bare, rough or sandblasted surfaces.

**VISCOSITY AT 75°F (24°C):** 70-80 KU

**AVERAGE DRY TIME 75°F:** Dries to touch in 30 minutes. Can re-coat in 4 hours. Allow 2 days for complete cure before putting back in service.

**RECOMMENDED REDUCER:** Water

**RECOMMENDED CLEAN UP:** Soap & Water

**RESISTANCE TO:** Chlorine, Alkali, Algae, Mineral Oils, Fresh and Salt Water

**RECOMMENDED PRIMER:** Pool Grip™ Waterbase Epoxy

**APPLICATION:** Brush, Spray or Roller (preferred)

**Roll:** 3/8" nap mohair metal, lambskin, phenolic core roller. Keep roller wet. Roll in one direction, rewet, then cross roll.

**Spray:** Conventional Air 50 -70 psi, Tip Size .055 -.070, Airless 2200- 2500 psi, Tip Size .019-.023.

**SURFACE PREPARATION:** Water blast the surface to remove all loose paint, dirt, oils and grease. Decks must be cleaned with a Tri-Sodium Phosphate (TSP) wash, scrubbing surface to get rid of oil, dirt and suntan lotions, and then etched with a 15-20% solution of muriatic acid. Then thoroughly rinse with TSP & flush with plenty of fresh water and allowed to dry thoroughly. Glossy surfaces should be power sanded to a 80 grit profile for proper adhesion.

**POT LIFE:** Not Applicable

**LIMITATIONS:** Do not apply if material, substrate or ambient temperature is below 50°F or above 95°F.

**SHELF LIFE:** Maximum 24 months if not subject to freezing.

**MIXING:** Mix very well for 10 minutes, apply as it comes from the container, and thin with water as needed for proper performance.

**PACKAGE:** 1 Gallon cans (2 per case), 5 gallon pails, 1 pint cans

Acrylic Resin	Proprietary
Diacetone Alcohol	123-42-2
Butyl Cellosolve	00111-76-2
Ethylene Glycol	107-21-1
Titanium Dioxide	13463-67-7
Talc	14807-96-6
Calcium Carbonate	1317-65-3

## NATIONAL POOL FINISHES

1999 ELIZABETH STREET, NORTH BRUNSWICK, N.J. 08902

(800) 628-8422

[www.bluewatermarinepaint.com](http://www.bluewatermarinepaint.com)

This product contains a maximum of 1.6 pounds of VOS per gallon of coating. Maximum VOC content 190 grams/liter.