



PUR-FECT PURGE® 34-3180

Flush Compound
March 2009

Flush Compound

PUR-FECT PURGE® is designed for flushing curing hot melt adhesive out of application equipment.

APPLICATION

When container of curing hot melt is empty, raise platen out of container and replace with container of 34-3180. Flush equipment by pumping 34-3180 through gun. PUR-FECT PURGE flows readily at 250°F.

Suggested application temperature is 250°F.

When ready to run again, raise platen out of container. Pump flush compound out of hose and gun. Remove any excess compound by means of a paint stirring stick or scraping tool and the equipment is ready for the next container of curing hot melt.

NOTE: PUR-FECT PURGE in straight-sided 55-gallon drums is designated as PUR-FECT PURGE® 34-3182.

PRECAUTIONS

Material is applied hot. Appropriate clothing and eye protection should be used.

Use with adequate ventilation to remove any hot melt fumes or vapors that are generated.

Keep containers and premelters covered to avoid contamination.

Rotate stock and use oldest material first.

Do not mix with other adhesives.

ISSUE: 01/05/04

Supersedes 05/20/02

TYPICAL PROPERTIES

APPEARANCE

Light lemon-colored solid

WEIGHT/GALLON

Approx. 8.0 lbs.

SOLIDS

100%

SOFTENING POINT

Approx. 200°F (Ball & Ring)

VISCOSITY

Approx. 15,000 cps @ 225°F

Approx. 4,600 cps @ 250°F

CONTAINERS

5 gallon pail

Also available: 55 gallon

straight-sided drum = 34-3182

Slats = 34-2952

READ PRECAUTIONS BEFORE USING ADHESIVE

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all**



warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

03/2009 cal

Henkel Americas
Tel: +1.800.797.4992, Fax: +1.609.409.5699

For the most direct access to local sales and technical support visit: www.henkelna.com/industrial