



Formula 610

DESCRIPTION

Formula 610 is superior for carton closing. It is a high output low viscosity adhesive with excellent wetting and rapid set under compression. It is specifically formulated for bonding paper and cardboard. Formula 610 meets mil spec AA 59692 (formerly MMM-A-250C).

NON-TOXIC

The components in Formula 610 have been analyzed by a qualified toxicologist and this product is certified to be non-toxic. Additionally, Formula 610 meets FDA CFR 175.105 adhesive requirements for indirect contact with food.

TYPICAL USES

Carton closing, quick temporary positioning of wooden components, cardboard, paper, porous substrates.


PRODUCT SPECIFICATIONS

Softening point	230°F (110°C)
Viscosity @ 350°F (176°C), centipoise	3,500
Specific gravity	0.98
Shear tensile strength on pine, psi	680
Adhesive tensile on pine, psi	244
Adhesive tensile on steel, psi	260
Hardness @ 72°F (25°C)	95
Heat resistance	145°F (63°C)
Open time (approx) seconds	35
Compression set time (seconds)	3-5

Test Method

ASTM E28-67
Brookfield Thermosel
ASTM 1475
ASTM D-1002
ASTM D-1344-78
ASTM D-1344-78
Shore "A"
AdTech
AdTech
AdTech

VISCOSITY PROFILE



APPLICATION

For optimum performance, Formula 610 should be applied in one of AdTech's reliable hand held hot melt applicators.

IMPORTANT NOTICE: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable but the accuracy of completeness thereof is not guaranteed, and the user should determine the suitability of the product for the intended use. AdTech disclaims any responsibility for any warranties of merchantability and fitness for purpose, verbal recommendations of its representatives and consequential damages.

Adhesive Technologies, Inc. / 3 Merrill Industrial Drive, Hampton, NH 03842 USA / Tel: 603 926 1616 / Fax: 603 926 1780