



**Specification Sheet
#738**

Type: Hot Melt Glue - Ethylene Vinyl Acetate

Solids: 100%

Viscosity ¹: @ 250° (F) (cps) 17,100
@ 325° (F) (cps) 4,310
@ 375° (F) (cps) 2,080

SAFT ²: 170° (F)

PAFT ³: 119° (F)

Open Time ⁴: 15 seconds

Mettler Softening Point ⁵: 205° (F)

Color: Amber

Odor: Slight

Shelf Life: Indefinite

Flash Point: Above 450° (F)

Storage: Common Storage

Application Temperature: 250° (F) to 380° (F)

Suggested Uses: All-temperature adhesive which has long open time. Good adhesion to wood; also used on carpets. Very good hot tack.

Precautions: Do Not Mix with other adhesives
Severe burns will result if contact is made in molten state.
Material safety data sheets provide safety precautions that should be observed in handling and storing.

The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. FPC warrants that the product conforms with FPC written specifications, and is free from defects. FPC disclaims all other warranties, expressed or implied, including the warranties of merchantability and fitness for a particular purpose. The buyer's sole remedy for non compliance with this warranty shall be for the replacement of the product or refund of the buyer's purchase price.

¹ Brookfield Viscosity – ASTM D3236 using spindle SC4-27

² Shear Adhesion Failure Temperature (SAFT) – ASTM D4498 – using 45# Kraft paper substrates, 500 g. weights

³ Peel Adhesion Failure Temperature (PAFT) – ASTM D4498 (modified for peel mode) – using 45# Kraft paper substrates, 100 g. weights

⁴ Open Time – ASTM D4497-94 (1999) – using 45# Kraft paper substrates

⁵ Mettler Softening Point – ASTM D6493-99