

Product Data Sheet

September 2015 Supersedes: June 2015

Product Description	3M [™] VHB [™] Tape 5906 is a thin foam tape with pressure sensitive adhesive on both sides, and are used for bonding a wide range of materials, including many paints and lower surface energy plastics in addition to metals and other plastics. The foam is comfortable to increase contact with the surfaces. This tape is similar to other products in the 3M [™] VHB [™] Tape 5952 family except thickness.	
Key Features	 providing adhesion to the broadest range of substrates, including most powder coated paints conformability to slightly mismatched or rigid surfaces 	
Physical Properties	Adhesive Type	Modified Acrylate
	Thickness ASTM D3652-01 Tape Liner Total (Tape + Liner)	0.15 mm ± 15% 0.08 mm 0.23 mm
	Release Liner	Clear Polyester
	Tape Colour	Black
	Density	750 kg/m ³ ± 10%
Performance Characteristics	Adhesion to Steel ASTM D3330 (90° Peel, after 72h dwell time)	15 N/cm
	Static Shear Strength ASTM D3654 10.000 min	23°C (1000g) 70°C (500g) 90°C (500g) 120°C (250g)
	Dynamic Shear Strength ASTM D1002	750 kPa
	Tensile Properties (T-Block) ASTM D897 (50mm / min)	690 kPa
	Temperature Performance ASTM D4498-7 (SAFT)	120°C (Long Term) 150°C (Short Term)

Application Temperature	Ideal application temperature range is 21°C to 38°C. Pressure sensitive adhesives use viscous flow to achieve substrate contact area. To obtain good performance with all 3M [™] VHB [™] Tapes, it is important to ensure that the surfaces are clean, dry and free of condensed moisture.
Shelf Life	All 3M [™] VHB [™] Tapes have a shelf life of 24 months from date of shipment when stored at 4°C to 38°C and 0-95% relative humidity. The optimum storage conditions are 22°C and 50% relative humidity. Performance of tapes is not projected to change even after shelf life expires; however, 3M does suggest that 3M [™] VHB [™] Tapes are used prior to the shelf life date whenever possible.
For Additional Information	To request additional product information or to arrange for sales assistance, please see below for contact details.
Important Notice	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law
Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations	

3M and VHB are trademarks of the 3M Company.

3M

3M Svenska AB Industri Bollstanäsvägen 3 191 89 Sollentuna Tel: 08-92 21 00 Fax: 08-92 22 88 E-post: kundservice@mmm.co <u>m</u> www.3M.se/tejp 3M a/s Industri Hannemanns Allé 53 2300 København S Tlf.: 43 48 01 00 Fax.: 43 20 15 65 E-mail: dkindustri@mmm.co m www.3Mindustri.dk 3M Norge AS Avd. Industri Hvamveien 6 2013 Skjetten Tel: 0 63 84 Fax: 63 84 17 88 E-post: Kundeservice@mmm.co m www.3M.no/tape

Suomen 3M Oy Teollisuustuotteet PL 600 Keilaranta 6 02151 Espoo Puh: 09-525 21 Fax: 09-525 2279 http://www.3M.fi/teollisuu s