



## Glue Dots

### LOW TACK GLUE DOT – APPROX 9MM DIA

TYPE	REMOVABLE PRESSURE SENSITIVE
THICKNESS OF ADHESIVE MM	0.43
PEEL ADHESION TO STEEL N/25MM	5.5 (20 MINUTES DWELLING TIME)
PEEL ADHESION TO STEEL PER DOT	2.4 (20 MINUTES DWELLING TIME)
SHEAR TO STEEL 230°C PER DOT (500G LOAD)	0.3 MINUTES
SHEAR AT 50°C PER DOT (250G LOAD)	0.4 MINUTES
SHEAR AT 80°C PER DOT (250G LOAD)	0.2 MINUTES
TEMPERATURE RANGE	-10 TO 60°C
	<b>DUE TO VARIATION IN THE SIZE OF THE DOTS, AND NATURE OF THE TESTING, RESULTS SHOULD BE TREATED AS APPROXIMATE.</b>
SUGGESTED USE	PAPER, PLASTIC ETC. USE ON LIGHTWEIGHT OBJECTS WHERE EASY RELEASE PROPERTIES ARE REQUIRED.
CHARACTERISTICS	SOFT ADHESIVE WITH LOW PEEL STRENGTH AND MEDIUM SHEAR STRENGTH
SUGGESTED HANDLING	READY FOR USE AS SUPPLIED. KEEP AWAY FROM DUST AND OIL
PRECAUTIONS	USE OLDEST STOCK FIRST. DISCARD UNUSED PRODUCT AFTER 18 MONTHS. THIS PRODUCT CONTAINS SOME OIL, TEST ABSORBENT SURFACES FOR BLEEDING.
	We are available to help purchasers obtain best results from information believed to be reliable. However we have no control over the conditions under which our products are transported, stored, handled or used by Purchasers and in any event all recommendations and sales are made on condition that we will not be held liable for any damages resulting from their use.

### HIGH TACK GLUE DOT – APPROX 9MM DIA

TYPE	REMOVABLE PRESSURE SENSITIVE
THICKNESS OF ADHESIVE MM	0.54
PEEL ADHESION TO STEEL N/25MM	47.5 (20 MINUTES DWELLING TIME)
PEEL ADHESION TO STEEL PER DOT	20.9 (20 MINUTES DWELLING TIME)
SHEAR TO STEEL 230°C PER DOT (500G LOAD)	12 MINUTES
SHEAR AT 50°C PER DOT (250G LOAD)	1.9 MINUTES
SHEAR AT 80°C PER DOT (250G LOAD)	0.8 MINUTES
TEMPERATURE RANGE	-10 TO 60°C
	<b>DUE TO VARIATION IN THE SIZE OF THE DOTS, AND NATURE OF THE TESTING, RESULTS SHOULD BE TREATED AS APPROXIMATE.</b>
SUGGESTED USE	PAPER, PLASTIC ETC. USE ON LIGHTWEIGHT OBJECTS WHERE SOME RELEASE PROPERTIES ARE REQUIRED.
CHARACTERISTICS	STIFF ADHESIVE WITH MEDIUM PEEL STRENGTH AND MEDIUM SHEAR STRENGTH
SUGGESTED HANDLING	READY FOR USE AS SUPPLIED. KEEP AWAY FROM DUST AND OIL
PRECAUTIONS	USE OLDEST STOCK FIRST. DISCARD UNUSED PRODUCT AFTER 18 MONTHS. THIS PRODUCT CONTAINS SOME OIL, TEST ABSORBENT SURFACES FOR BLEEDING.
	We are available to help purchasers obtain best results from information believed to be reliable. However we have no control over the conditions under which our products are transported, stored, handled or used by Purchasers and in any event all recommendations and sales are made on condition that we will not be held liable for any damages resulting from their use.

### SUPER HIGH TACK GLUE DOT – APPROX 9MM DIA

TYPE	PERMANENT PRESSURE SENSITIVE
THICKNESS OF ADHESIVE MM	0.42
PEEL ADHESION TO STEEL N/25MM	79.2 (20 MINUTES DWELLING TIME)
PEEL ADHESION TO STEEL PER DOT	31.7 (20 MINUTES DWELLING TIME)
SHEAR TO STEEL 230°C PER DOT (500G LOAD)	21 MINUTES
SHEAR AT 50°C PER DOT (250G LOAD)	2.8 MINUTES
SHEAR AT 80°C PER DOT (250G LOAD)	0.9 MINUTES
TEMPERATURE RANGE	-10 TO 60°C
	<b>DUE TO VARIATION IN THE SIZE OF THE DOTS, AND NATURE OF THE TESTING, RESULTS SHOULD BE TREATED AS APPROXIMATE.</b>
SUGGESTED USE	PAPER, PLASTIC, WOOD, METAL ETC.
CHARACTERISTICS	SOFT ADHESIVE WITH HIGH PEEL STRENGTH AND HIGH SHEAR STRENGTH
SUGGESTED HANDLING	READY FOR USE AS SUPPLIED. KEEP AWAY FROM DUST AND OIL
PRECAUTIONS	USE OLDEST STOCK FIRST. DISCARD UNUSED PRODUCT AFTER 18 MONTHS. THIS PRODUCT CONTAINS SOME OIL, TEST ABSORBENT SURFACES FOR BLEEDING.
	We are available to help purchasers obtain best results from information believed to be reliable. However we have no control over the conditions under which our products are transported, stored, handled or used by Purchasers and in any event all recommendations and sales are made on condition that we will not be held liable for any damages resulting from their use.