



#JWT LT

#JWT LT

Indoor Low tack fine line masking tape

Tape Structure

Backing JAPANESE WASHI PAPER

Adhesive ACRYLIC CLEAR ADHESIVE

Characteristic

JWT LT is able to ensure high performances when **blade-sharp painting** works are required . It is **mostly suitable for delicate surfaces** where low tack and adhesion performances are required, like on **wallpaper, last touches & adjustments** and **restoration works**

Suggested **application** time **at least after 40 minutes** from previous paint application in standard indoor temperature conditions.

Especially suited for a variety of indoor paint works allowing **easy indoor removability up to 15 days** after application and **1 week UV resistance**.

CHARACTERISTICS	UNITS	STD. VALUES	TOLER.	TEST METHOD
Total Weight	g/m2	70	± 10%	ISO 536
Total Thickness	µm	75	± 10%	AFERA 5006
MD tensile strength	N/cm	> 25		AFERA 5004
MD elongation at break	%	> 3		AFERA 5004
Adhesion to steel plate	N/cm	> 0,9		AFERA 5001

Available colours: VIOLET
 Removal without residual (indoor): 15 days
 UV resistance: 7 days
 Fine line extreme precision

Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. All information has to be intended as generic advise for the use of products. Users have to verify the suitability of each tape in actual application under specific conditions.



#JWT LT

Indoor Low tack fine line masking tape

Application fields



Technical Features



Terms & Conditions of liability

PPM tapes must be stored in a dry location, protected from direct sunlight exposure and from freezing. Storage temperatures should be as close as possible to room temperature; suggested storage temperature should range from 15 to 25°C with max. relative humidity of 60%.

Make sure the surface you wish to place the tape on is cleaned, dried and free from oil and dust. It is suggested not to apply the tape with temperatures lower than 10°C. With a storage temperature lower than 10°C, it is always suggested temperature reconditioning of the tape at room temperature (15°C - 25 °C) before its use. Shelf life from date of manufacture: (no yellowing and < 10% loss in performance at 23 °C, 50 % humidity) is considered 12 months for Slit rolls and 6 for Jumbo rolls PPM does not take responsibility for the defective material is not stored and used in accordance with the conditions listed above.