

Polypropylene Acrylic: Stock Texts

Technical Specifications

Adhesive	Acrylic
Film Thickness	25m μ
Adhesive Coat Weight	15-18g/m ²
Total Thickness	46 m μ (\pm 5 %)
Adhesion to Steel	3,1 – 3,6 N/2,5 cm
Tack Rolling	9-12 cm
Elongation at Break	180-200 %
Holding Power (10mm,1kg)	2,2-3,0 h

Stocking time

We recommend using the product within 6 months from the delivery

Stocking Conditions

The product has to be stocked in a dry environment, at a temperature between 15°C and 25°C. The product must be stored protected from dust, humidity and direct sun exposure. It must be stored horizontally and kept in the original packaging

Use

Prior to use, carefully check that the contact surfaces are totally dry and clean from oil, grease and dust.

If the storage temperature has been different from what suggested, bring the tape to the temperature before application

The mentioned data stem from an average analysis carried out on our standard production and may undergo unexpected changes. Therefore they are not binding for our company

www.vikingtapes.co.uk

Tel: 01535 610373 - Fax: 01535 610801 - Email: sales@vikingtapes.co.uk

Unit 1, Coronation Business Park, Hard Ings Road, Keighley, West Yorkshire, BD21 3ND

3M Authorised
Distributor



Certificate No 16175
ISO 9001
ISO 14001

Polypropylene Acrylic: Stock Texts

Technical Specifications

Adhesive	Acrylic
Film Thickness	25m μ
Adhesive Coat Weight	15-18g/m ²
Total Thickness	46 m μ (\pm 5 %)
Adhesion to Steel	3,1 – 3,6 N/2,5 cm
Tack Rolling	9-12 cm
Elongation at Break	180-200 %
Holding Power (10mm,1kg)	2,2-3,0 h

Stocking time

We recommend using the product within 6 months from the delivery

Stocking Conditions

The product has to be stocked in a dry environment, at a temperature between 15°C and 25°C. The product must be stored protected from dust, humidity and direct sun exposure. It must be stored horizontally and kept in the original packaging

Use

Prior to use, carefully check that the contact surfaces are totally dry and clean from oil, grease and dust.

If the storage temperature has been different from what suggested, bring the tape to the temperature before application

The mentioned data stem from an average analysis carried out on our standard production and may undergo unexpected changes. Therefore they are not binding for our company

www.vikingtapes.co.uk

Tel: 01535 610373 - Fax: 01535 610801 - Email: sales@vikingtapes.co.uk

Unit 1, Coronation Business Park, Hard Ings Road, Keighley, West Yorkshire, BD21 3ND

3M Authorised
Distributor



ISO 9001
ISO 14001