



Product datasheet Issue No. 5 Issued Mar 2022

RA 8030 DOUBLE-SIDED HIGH PERFORMANCE SOLVENT ACRYLIC WHITE PVC FILMIC TAPE

TECHNICAL DETAILS		TYPICAL VALUE	<u>UNITS</u>
Thickness, adhesive + carrier Release liner thickness		0.275 0.66	mm mm
180 degree peel adhesion:	Open side Liner side	1200 1200	N/m N/m
Polyester loop tack:	Open side Liner side	1250 1250	N/m N/m
Liner release		90	gsm
Tensile strength		2000	N/m
Elongation at break		75	%
Static shear, 23 deg. C, 1Kg, 25mm square 23 deg. C, 2 Kg 25mm square		>100 55	h. h.
Shear adh. failure temperature	100g load 250g load	>100 >100	deg. C. deg. C.
Minimum application temperature		10	deg. C.
Service temperature		-20 to +120 (140 Short term)	deg. C.
Shelf life		12	Months

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETEMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



PAL ADHESIVE PRODUCTS Ltd

Darlaston Rd industrial Estate, Darlaston Rd, Wednesbury, WS10 7TN UK.

Email: sales@paladhesives.co.uk

Tel: +44 (0)121 - 526 5151 Fax: +44(0)121 - 568 - 6797