Test Methods: BS 7116

Unit 1, Coronation Business Park, Hard Ings Road, Keighley, West Yorkshire, BD21 3ND

VK2058 Carpet Tape

TECHNICAL DETAILS		TYPICAL VALUE	UNITS
Thickness, adhesive + carrier Release liner thickness		0.240 0.080	mm mm
180 degree peel adhesion:	Open side Closed side	600 600	N/m N/m
Polyester loop tack:	Open side Closed side	700 700	N/m N/m
Liner release		30	N/m
Tensile strength		1300	N/m
Elongation at break		6	%
Service temperature		-10 to +60	Deg. C.
Recommended application temperature		+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.		20	Hours
Shelf life		12	Months

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETEMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.