



VK3220 Double Sided Tape

<u>TECHNICAL DETAILS</u>		<u>TYPICAL VALUE</u>	<u>UNITS</u>
Thickness, adhesive + carrier		0.050	mm
Release liner thickness		0.075	mm
180 degree peel adhesion:	Open side	400	N/m
	Closed side	150	N/m
Polyester loop tack:	Open side	800	N/m
	Closed side	100	N/m
Liner release		10	N/m
Tensile strength		4600	N/m
Elongation at break		12	%
Service temperature		-20 TO +120	Deg. C.
Recommended application temperature		+5 TO +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.		>2	Hours
Shelf life		12	Months
Test Methods: BS 7116			

.THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
.DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES