

Test Report No. CANEC2001206601 Date: 21 Jan 2020 Page 1 of 3

ESSENERGY INC.

1765 LANDESS AVE., SUITE 34, MILPITAS. CA 95035

The following sample(s) was/were submitted and identified on behalf of the clients as : CLAY STOCK POT AND MULTI-CROCKS VM7800-5C

SGS Job No.: CP20-002822 - GZ

Date of Sample Received: 17 Jan 2020

Testing Period: 17 Jan 2020 - 21 Jan 2020

Test Requested: Selected test(s) as requested by client.

Test Method: Please refer to next page(s).

Test Results: Please refer to next page(s).

Result Summary:

Test Requested	Conclusion
US FDA CPG Sec. 545.400 (CPG 7117.06) and CPG Sec. 545.450 (CPG 7117.07) Pottery (Ceramics) and California Tableware Safety Law – Leachable	PASS
Lead and Cadmium Content (Internal surface)	

Signed for and on behalf of SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch

Ivy Ren

Approved Signatory



Test Report No. CANEC2001206601 Date: 21 Jan 2020 Page 2 of 3

Test Results:

Test Part Description:

Specimen No. SGS Sample ID Description Material

(claimed by the client)

SN1 CAN20-012066.001 Red-brown pot RED CLAY

US FDA CPG Sec. 545.400 (CPG 7117.06) and CPG Sec. 545.450 (CPG 7117.07) Pottery (Ceramics) and California Tableware Safety Law - Leachable Lead and Cadmium Content (Internal surface)

Test Method: With reference to AOAC 18th Ed. (2005) Section 973.32. Analysis was performed by

ICP-OES.

Sample 001 Large hollowware

	Extract Volume	<u>Depth</u>
	<u>(mL)</u>	<u>(mm)</u>
1	5000	140
2	5000	140
3	5000	140
4	5000	140
5	5000	140
6	5000	140

	Leachable Lead (µg/mL)	Leachable Cad- mium (µg/mL)
1	<0.05	<0.01
2	<0.05	<0.01
3	<0.05	<0.01
4	<0.05	<0.01
5	<0.05	<0.01
6	<0.05	<0.01
Limit	1.0	0.25

## Notes:

Flatware: Ceramic articles which have an internal depth, as measured from the lowest point to the horizontal plane passing through the upper rim, that does not exceed 25 mm.

Hollowware: Ceramic articles having an internal depth, as measured from the lowest point to the horizontal plane passing through the upper rim, greater than 25 mm.

Small hollowware: A capacity of less than 1.1 liter.

Large hollowware: A capacity of 1.1 liter or more.

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.ags.com/en/Terma-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.ags.com/en/Terma-and-Conditions/Terma-e-Document.aspx, subject to Terms and Conditions for Electronic Documents and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's influence of the Company and the Client's and documents. This document does not exceed the responsibility is to its Client and the document in this document to appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN, Doccheck-Bass.com