



8071

CRACK STOPPER DRIVEWAY PATCH Data Sheet

DESCRIPTION: Gardner Driveway Patch is a ready to use cement textured patching compound. It is a latex fortified and provides a long lasting durable patch that resists gas, oil and chemical deterioration. Use Gardner Driveway Patch to repair small holes and cracks (up to 3" deep) or to smooth out surfaces that are damaged by gasoline and oil spillage. Dries black.

PREPARATION: Use Driveway Klean™ prior to applying driveway patches and coating to surface to remove dirt, and light oil stains. This degreaser will allow for much improved adhesion of driveway sealers. On heavier oil stains, apply liberally and scrub area for best results. Rinses thoroughly with water leaving no puddles. Remove any loose and flaking material from area prior to application.

APPLICATION: Apply product on a clear, warm, sunny day when surface temperature is at least 65° and rising. Mix contents to a uniform consistency and apply to dampened surface. Do not apply to cracks or holes which have water puddles. Use trowel or putty knife to apply Driveway Patch to problem areas, ending with a smooth surface finish. For repairs or depths greater than 1", it is recommended that the compound be applied in layers. This will assure proper drying and strength. Area is ready to be sealcoated in approximately 24 hours.

DO NOT APPLY AT TEMPERATURES BELOW 50°F
DO NOT ALLOW STORED PRODUCT TO FREEZE

COVERAGE RATE: Approximately 10 lbs. will patch an area 10 sq. ft. x 1/8 inch deep.

CLEAN-UP: Clean tools with soap and water when wet, or an orange citrus cleaner when cured.

REGULATORY/ENVIRONMENTAL CHARACTERISTICS:

Volatile Organic Compound	2 g/l max. (.02 lbs/gal)
HMIS Rating	H-1, F-1, R-0
RCRA Hazardous Substances	NONE
SARA Title III listing:	
Sec. 302 Extremely Hazardous Substances	no
CERCLA Hazardous Substances	no
Sec. 313 Toxic Chemicals	no
SARA SEC. 311 & 312: Acute Hazard, Presence of Petroleum Distillates	

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS

Weight Per Gallon, lbs.	15.5 lbs.
Residue by Evaporation, %	90 min.
Combustible Solvents	None
Consistency	Trowel
Cure Time (at recommended coverage)	24 hours
Application Temperatures	65°F and rising
Flammability (Flash point, °F solvent)	N/A
Clean-up Tools	Soap and water when wet Orange citrus cleaner when cured

Approx. Shipping Weights: (Note: All approx. weights include container.)

1 gal. pail	10 lbs. (4.5 kg)
-------------	------------------

DANGER! HARMFUL OR FATAL IF SWALLOWED EYE, SKIN AND RESPIRATORY IRRITANT DO NOT INGEST

PRECAUTIONS: Keep away from heat and flame. **In Case Of: EYE CONTACT:** Flush immediately with plenty of water for at least 15 minutes and get medical attention. **SKIN CONTACT:** Wash thoroughly with soap and water. **INGESTED:** If swallowed INDUCE VOMITING. Seek medical attention immediately. **IRREGULAR OR STOPPED BREATHING:** Administer oxygen, start resuscitation. Use with adequate ventilation. Avoid prolonged breathing of vapor or spray mist. Wearing of gloves is recommended.

ASPHALT	CAS# 8052-42-4
CLAY	CAS# 1332-58-7
SAND	CAS# 14808-60-7
WATER	CAS# 7732-18-5
Product is asbestos free	
PATENT PENDING	

©2005 Gardner Asphalt Corporation
Manufactured by/Fabricado por: Gardner Asphalt Corporation,
P.O. Box 5449, Tampa, FL 33675

WARRANTY AND DISCLAIMER:

For limited warranty and disclaimer information, contact the Gardner-Gibson, Inc. corporate office at 1-800-237-1155 or www.gardner-gibson.com.

See SDS for more info

Gardner-Gibson, Inc. • P.O. Box 5449 • Tampa, Florida 33675-5449
Phone: (813) 248-2101 • Fax (813) 248-6768 • www.gardner-gibson.com