

Greenhouse Flooring Fabric

Series: Greenhouse Flooring Fabric - Nursery Grade

Recommended Applications: Greenhouse Flooring - Pedestrian Foot Traffic

Fabric Property	Test Method	Units	Minimum Average Roll Value
Weight (Typical)	ASTM D 5261	Oz yd ²	3.0 oz
Grab Tensile	ASTM D 4632	lbs	150 x 110
Grab Elongation	ASTM D 4533	%	15
Trap Tear	ASTM D 4533	lbs	60
CBR Puncture	ASTM D 6241	lbs	500
Thickness	ASTM D-1777	mils	15
Water Flow Rate	ASTM D 4491	gpm/sf	9
UV Resistance	ASTM D 4355	%	70- After 2500 hours

To the best of our knowledge, the information contained herein is accurate. However, Paramount Materials cannot anticipate all conditions under which the above product information and the products which we distribute or the products of other distributors or manufacturers in combination with the products which we offer, may be used. We accept no responsibility for results obtained by the application of this information or the safety or suitability of the products we distribute either alone or in combination with other products. Final determination of the suitability of any information or material for the used contemplated, or its manner of use, and whether the suggested use infringes any patents is the sole responsibility of the user.

Please note: Paramount Materials is a distributor of geotextile fabric, not the manufacturer. We source material from a number of different United States based geotextile manufacturers.