

Non-Woven Geotextile Fabric - PNW80

Series: Drainage & Filtration - Heavy-Duty

Recommended Applications: Drainage, Filtration, Erosion Control

Fabric Property	Test Method	Units	Minimum Average Roll Value
Grab Tensile	ASTM D 4632	lbs.	160
Grab Elongation	ASTM D 4632	lbs.	50
Trap-Tear Strength	ASTM D 4533	lbs.	65
CBR Puncture Strength	ASTM D 6241	lbs.	410
Mullen Burst Strength	ASTM D 3786	psi	315
Puncture	ASTM D 4833	lbs.	90
Permittivity	ASTM D 4491	sec ⁻¹	1.6
Water Flow	ASTM D 4491	gpm/ft ²	110
UV Resistance	ASTM D 4355	%	70
AOS	ASTM D 4751	US Sieve	#70

To the best of our knowledge, the information contained herein is accurate. However, Paramount Materials cannot anticipate all conditions under which the above product information and the products which we distribute or the products of other distributors or manufacturers in combination with the products which we offer, may be used. We accept no responsibility for results obtained by the application of this information or the safety or suitability of the products we distribute either alone or in combination with other products. Final determination of the suitability of any information or material for the used contemplated, or its manner of use, and whether the suggested use infringes any patents is the sole responsibility of the user.

Please note: Paramount Materials is a distributor of geotextile fabric, not the manufacturer. We source material from a number of different United States based geotextile manufacturers.