

Mirafi[®] 1120N



Mirafi[®] 1120N is a needlepunched nonwoven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. Mirafi[®] 1120N is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas Laboratories are Geosynthetic Accreditation Institute – Laboratory Accreditation Program (<u>GAI-LAP</u>).

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs (N)	300 (1335)	300 (1335)
Grab Tensile Elongation	ASTM D4632	%	50	50
Trapezoid Tear Strength	ASTM D4533	lbs (N)	115 (512)	115 (512)
CBR Puncture Strength	ASTM D6241	lbs (N)	800 (3560)	
			Maximum O	pening Size
Apparent Opening Size (AOS)	ASTM D4751	U.S. Sieve (mm)	100 (0.15)	
			Minimum I	Roll Value
Permittivity	ASTM D4491	Sec ⁻¹	0.8	
Flow Rate	ASTM D4491	gal/min/ft ² (l/min/m ²)	65 (2648)	
			Minimum T	est Value
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	70	

Physical Properties	Unit	Roll Size
Roll Dimensions (width x length)	ft (m)	15 x 300 (4.57 x 91.4)
Roll Area	yd² (m²)	500 (418)

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi[®] is a registered trademark of Nicolon Corporation

Copyright © 2015 Nicolon Corporation. All Rights Reserved.

365 South Holland Drive Pendergrass, GA 30567 Tel 706 693 2226 Tel 888 795 0808 Fax 706 693 4400 www.tencate.com



FGS000357 ETQR29

GAI-LAP-25-97



TENCATE GEOSYNTHETICS Americas

365 South Holland Drive Pendergrass, GA 30567

FGS000357 ETQR29 Tel 706 693 2226 Tel 888 795 0808 Fax 706 693 4400 www.tencate.com



GAI-LAP-25-97