

Mirafi[®] S800



Mirafi[®] S800 is a needlepunched nonwoven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. Mirafi[®] S800 is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

| Mechanical Properties | Test Method | Unit | Minimum Average Roll Value |
|------------------------------|-------------|---|-----------------------------|
| Weight | ASTM D5261 | oz/yd ² (g/m ²) | 8.0 (271) |
| Thickness | ASTM D5199 | mils (mm) | 90 (2.3) |
| Grab Tensile Strength | ASTM D4632 | lbs (N) | 230 (1024) |
| Grab Tensile Elongation | ASTM D4632 | % | 50 |
| Trapezoid Tear Strength | ASTM D4533 | lbs (N) | 95 (423) |
| CBR Puncture Strength | ASTM D6241 | lbs (N) | 600 (2670) |
| | | | Maximum Opening Size |
| Apparent Opening Size (AOS) | ASTM D4751 | U.S. Sieve (mm) | 100 (0.15) |
| | | | Minimum Roll Value |
| Permittivity | ASTM D4491 | sec ⁻¹ | 1.4 |
| Permeability | ASTM D4491 | cm/sec | 0.31 |
| Flow Rate | ASTM D4491 | gal/min/ft ² (l/min/m ²) | 110 (4481) |
| | | | Minimum Test Value |
| UV Resistance (at 500 hours) | ASTM D4355 | % strength retained | 80 |

| Physical Properties | Unit | Roll Value |
|----------------------------------|-----------------------------------|---------------------|
| Roll Dimensions (width x length) | ft (m) | 15 x 300 (4.5 x 91) |
| Roll Area | yd ² (m ²) | 500 (418) |

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi[®] is a registered trademark of Nicolon Corporation.

Copyright © 2013 Nicolon Corporation. All Rights Reserved.

365 South Holland Drive
Pendergrass, GA 30567

Tel 706 693 2226
Tel 888 795 0808

Fax 706 693 4400
www.tencate.com

FGS000348
ETQR22



GAI-LAP-25-97