

Mirafi® TM14S

Mirafi[®] TM14S is a 3-dimensional, lofty synthetic, erosion control mat, which provides bare soil retention, vegetation nurturing and turf reinforcement. Mirafi[®] TM14S is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (<u>GAI-LAP</u>).

| Performance Properties | Test Method | Unit | Value |
|----------------------------------------|-------------|-----------------|------------|
| Overtopping Discharge (Q) ¹ | Large Scale | cfs/ft² (ls/m²) | 4.0 (1219) |
| Manning's Coefficient ² | Calculated | "n" | 0.033 |

| Mechanical Properties | Test Method | Unit | MARV | |
|--------------------------------|-------------|---------------------------------------|--------------------|-------------|
| | | | MD | CD |
| Tensile Strength @ Ultimate | ASTM D6818 | lbs/ft (kN/m) | 3000 (43.8) | 2400 (35.0) |
| | | Minimum Test Value | | |
| UV Resistance (at 3000 hours) | ASTM D4355 | % strength retained | 95 | |
| UV Resistance (at 6000 hours) | ASTM D4355 | % strength retained | 90 | |
| UV Resistance (at 10000 hours) | ASTM D4355 | % strength retained | 80 | |
| | | | Typical Roll Value | |
| Resiliency ³ | ASTM D6524 | mils (mm) | 330 (8.4) | |
| Thickness | ASTM D6525 | mils (mm) | 475 (12.1) | |
| | | | Maximum Roll Value | |
| | | | MD | CD |
| Tensile Elongation | ASTM D6818 | % | 50 | 50 |
| Light Penetration | ASTM D6567 | % | 40 | |
| | | | Minimum Roll Value | |
| Physical Properties | Test Method | Unit | MARV | |
| Mass Per Unit Area | ASTM D6566 | oz/yd² (g/m²) | 8.5 (288) | |
| Color: Green | | Roll Sizes: 12' x 75' (3.66m x 22.9m) | | |

¹Based on 3:1 Bed Slope.

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi® is a registered trademark of Nicolon Corporation.

Copyright © 2016 Nicolon Corporation. All Rights Reserved.





² Higher Manning's Coefficient will result in reduced flow velocity.

³ Typical Resiliency Thickness reported in mils, *Tf* per Section 9.5, ASTM D6524.