

Applicant: SUNNYLIFE GROUP PTY LTD

**B1 85 DUNNING AVENUE** 

**ROSEBERY** NSW 2018 **AUSTRALIA** 

Attn: **NOLIA CHIU** 

Jul 05, 2023 Date:

Sample and Information provided by customer

Item Name Quantity **Beach Bats** 

6 sets

SCBPSPGE (range book SBPSCBL)

Item No.
Labelled Age Group
Packaging Provided
Country of Origin 6+ years Yes China

For and on behalf of: Intertek Testing Services HK Ltd.





HKGH0302244802

Number:





Number: HKGH0302244802

### Conclusion:

The submitted sample was tested under the following requirements requested by the applicant, subject to the information stated in the remark and attached page(s) for details:

<u>Requirement</u> Result EN 71-1:2014 + A1:2018 (1) **Pass**  Mechanical and physical properties (2) UKCA mark checking See details enclosed (3) EN 71-2:2020 Pass - Flammability Test (4) EN 71-3: 2019 + A1: 2021 **Pass** - Migration of certain elements (5) Regulation (EC) No. 1907/2006 on REACH Annex XVII as amended by Commission **Pass** Regulation (EU) No. 835/2012 and Commission Regulation (EU) 2016/217 - Cadmium content requirement (6) Cadmium Content Requirement in Annex XVII Entry 23 of the REACH Regulation (EC) No Pass 1907/2006 and Amendment (EC) No 552/2009, (EÚ) No 494/2011, (EU) No 835/2012 and (EU) 2016/217 & The REACH etc. (Amendment etc.) (EU Exit) Regulations 2019 (S.I. 2019 - Cadmium content requirement (7) REACH Regulation (EC) no. 1907/2006 & amendment (EU) no. 1272/2013 Annex XVII **Pass** Item 50 - Polycyclic aromatic hydrocarbons content (8) REACH Regulation (EC) no. 1907/2006 & amendment no. 1272/2013, Annex XVII, Item 50 Pass & The REACH etc. (Amendment etc.) (EU Exit) Regulations 2019 (S.I. 2019 No. 758) as - Polycyclic aromatic hydrocarbons content (9) REACH Regulation (EC) no. 1907/2006, Annex XVII Items 51 & 52, amendment no. **Pass** 552/2009 & 2018/2005 - Phthalates content (10) REACH Regulation (EC) no. 1907/2006, Annex XVII, Item 51 & 52 & amendment no. Pass 552/2009 & 2018/2005 & The REACH etc. (Amendment etc.) (EU Exit) Regulations 2019

Decision Rule(s):

When a statement of conformity to a specification or standard is provided on test report, the decision rule shall be applied. For details, please refer to Intertek's "Decision Rule Document" and is available on Intertek's website. <a href="https://intertekhk.grd.by/decision-rule-doc.">https://intertekhk.grd.by/decision-rule-doc.</a>.

If decision rule already inhered in the requested specification or standard, Intertek's "Decision Rule Document" is not applicable and indication of "" was shown as above table.

(N)

(S.I. 2019 No. 758) as amended

- Phthalates content



Number: HKGH0302244802

### (1) Mechanical and Physical Test

Test Standard : European Standard on Safety of toys EN 71-1:2014 + A1:2018

Age group for testing : For Ages Over 6 Years

Clause	Requirement	Assessment
4	General requirements	
4.1	Material cleanliness	Р
4.2	Assembly	NA
4.3	Flexible plastic sheeting	NA
4.4	Toy bags	NA
4.5	Glass	NA
4.6	Expanding Materials	NA
4.7	Edges	P
4.8	Points and Metallic wires	P
4.9	Protruding parts	NA NA
4.10	Parts moving against each other	NA NA
4.11	Mouth actuated toys and other toys intended to be put into mouth	NA NA
4.11 4.12	Balloons	NA NA
4.12 4.13		NA NA
4.13	Cords of toy kites and other flying toys	
4.14	Enclosures	NA NA
4.15	Toys intended to bear the mass of a child	NA NA
4.16	Heavy immobile toys	NA B
4.17	Projectiles	P
4.18	Aquatic toys and inflatable toys	NA
4.19	Percussion caps specifically designed for use in toys and toys using percussion caps	NA
4.20	Acoustics	NA
4.21	Toys containing non -electrical heat source	NA
4.22	Small balls	Р
4.23	Magnets	NA
4.24	Yo-yo balls	NA
4.25	Toy's attached to food	NA
4.26	Toy Disguise Costumes	NA
4.27	Flying toys	NA
5	Toys intended for children under 36 months	
5.1	General requirements for toys intended for children under 36 months	NA
5.2	Soft-filled toys and soft-filled parts of a toy	NA
5.3	Plastic sheeting	NA NA
5.4	Cords, chains and electrical cables in toys	NA NA
5.5	Liquid filled toys	NA NA
5.6	Speed limitation of electrically driven ride-on toys	NA NA
5.7	Glass and porcelain	NA NA
5.8	Shape and size of certain toys	NA NA
5.0 5.9	Toys comprising monofilament fibres	NA NA
5.10	Small balls	NA NA
5.10	Play figures	NA NA
5.11 5.12	Hemispheric-shaped toys	NA NA
5.12 5.13	Suction cups	NA NA
		NA NA
5.14	Straps intended to be worn fully or partially around the neck	
5.15	Sledges with cords for pulling (7.24)	NA D
6	Packaging	Р





Kowloon, Hong Kong



Number: HKGH0302244802

Clause	Requirement	Assessment
7	Warnings, markings and instructions for use	
7.1	General	Р
7.2	Toys not intended for children under 36 months	Р
7.3	Latex balloons	NA
7.4	Aquatic toys	NA
7.5	Functional toys	NA
7.6	Hazardous sharp functional edges and points	NA
7.7	Projectile Toys	NA
7.8	Imitation protective masks and helmets	NA
7.9	Toy kites	NA
7.10	Roller skates, inline skates, skateboards and certain other ride-on toys	NA
7.11	Toys intended to be attached to or strung across a cradle, cot, or perambulator	NA
7.12	Liquid-filled teethers	NA
7.13	Percussion caps specifically designed for use in toys	NA
7.14	Acoustics	NA
7.15	Toy bicycles	NA
7.16	Toys intended to bear the mass of a child	NA
7.17	Toys comprising monofilament fibres	NA
7.18	Toy scooters	NA
7.19	Rocking horses and similar toys	NA
7.20	Magnetic / electrical experimental sets	NA
7.21	Toys with electrical cables exceeding 300 mm in length	NA
7.22	Toys with cords or chains intended for children of 18 months and over but under 36 months	NA
7.23	Toys intended to be attached to a cradle, cot or perambulator	NA
7.24	Sledges with cords for pulling	NA
7.25	Flying toys	NA
7.26	Improvised projectiles	NA

Abbreviation: P = Pass NA = Not Applicable







Number: HKGH0302244802

Below are additional information according to the Toy Safety Directive 2009/48/EC requirement. These information also appears as a note within the EN71 but are not standard requirements and not accredited:

The manufacturer's and importer's name, registered trade name or registered trade mark, the address and type, batch, serial or model number or other element allowing their identification shall be indicated on the product itself. In addition, toys or packagings shall also bear the CE-marking. After checking, it was found that

	Toy	Packaging
Manufacturer's name	Present	Present
Manufacturer's address	Absent	Present
EU Importer's name	Present	Present
EU Importer's address	Absent	Present
Product identification code	Absent	Present
CE-marking	Present (not in correct format)	Present

Date sample received: Jun 13, 2023 Test Period: Jun 13, 2023 to Jun 19, 2023





2/F Garment Centre

576 Castle Peak Road

Kowloon, Hong Kong



Number: HKGH0302244802

#### (2)UKCA mark checking

Below is additional information checking according to the UK Toy (Safety) Regulations requirement. The checking is not within accreditation scope.

The manufacturer's and importer's name, registered trade name or registered trademark, the address and type, batch, serial or model number or other element allowing their identification shall be indicated on the product itself.

After checking, it was found that

	Toy	Packaging
Name of authorised representative in Great Britain	Present	Present
Address of authorised representative in Great Britain	Absent	Present
Product identification code	Absent	Present

With reference to the guidance of using UKCA marking from 1 January 2021 by the Department for Business, Energy and Industrial Strategy published on 1 September 2020, toys or packagings shall also bear the UKCA marking. However, as per the official publishment on 14 November 2022, CE marking is continued to be recognised for 2 more years in UK market until 31 December, 2024.

After checking, it was found that

	Toy	Packaging
UKCA marking	Present (not in correct format)	Present
	ioiillat)	

Date sample received: Jun 13, 2023 Test Period: Jun 13, 2023 to Jun 19, 2023







Number: HKGH0302244802

### (3) Flammability Test

Test Standard : European Standard on Safety of Toys EN 71-2:2020

<u>Clause</u>	Requirement	<u>Assessment</u>
4.1	General requirements	Р
4.2	Toys to be worn on the head	NA
4.3	Toy disguise costumes and toys intended to be worn by a child in play	NA
4.4	Toys intended to be entered by a child	NA
4.5	Soft filled toys	NA

Abbreviation: P = Pass NA = Not Applicable

Date sample received : Jun 13, 2023 Test Period : Jun 13, 2023 to Jun 19, 2023



Kowloon, Hong Kong



Number: HKGH0302244802

### (4) 19 Toxic Element Migration Test

Test Method : EN 71-3 : 2019 + A1 : 2021. Acid extraction method was used and toxic elements

content were determined by Inductively Coupled Argon Plasma Spectrometry and Ion

Chromatography- Inductively Coupled Plasma-Mass Spectrometry and/or Gas

Chromatographic - Mass Spectrometry

### Category (III): Scraped-off toy material:

		Result (mg/kg)		Limit
	(1)	(2)	(3)	(mg/kg)
Soluble Aluminium (AI)	<300	<300	870	28130
Soluble Antimony (Sb)	<10	<10	<10	560
Soluble Arsenic (As)	<10	<10	<10	47
Soluble Barium (Ba)	<10	<10	<10	18750
Soluble Boron (B)	<50	<50	<50	15000
Soluble Cadmium (Cd)	<5	<5	<5	17
Soluble Chromium (III) (Cr III)	<10	<10	<10	460
Soluble Chromium (VI) (Cr VI)	< 0.025	<0.025	<0.025	0.053
Soluble Cobalt (Co)	<10	<10	<10	130
Soluble Copper (Cu)	<10	<10	<10	7700
Soluble Lead (Pb)	<10	<10	<10	23
Soluble Manganese (Mn)	19	<10	<10	15000
Soluble Mercury (Hg)	<10	<10	<10	94
Soluble Nickel (Ni)	<10	<10	<10	930
Soluble Selenium (Se)	<10	<10	<10	460
Soluble Strontium (Sr)	<100	<100	<100	56000
Soluble Tin (Sn)	<10	<10	<10	180000
Soluble Organic tin ++	<5.0	<5.0	<5.0	12
Soluble Zinc (Zn)	470	430	410	46000





Page 8 of 27



	Result (mg/kg)			Limit
	(4)	(5)	(6)	(mg/kg)
Soluble Aluminium (AI)	520	<300	450	28130
Soluble Antimony (Sb)	<10	<10	<10	560
Soluble Arsenic (As)	<10	<10	<10	47
Soluble Barium (Ba)	<10	<10	<10	18750
Soluble Boron (B)	<50	<50	<50	15000
Soluble Cadmium (Cd)	<5	<5	<5	17
Soluble Chromium (III) (Cr III)	<10	<10	<10	460
Soluble Chromium (VI) (Cr VI)	<0.025	<0.025	<0.025	0.053
Soluble Cobalt (Co)	<10	<10	<10	130
Soluble Copper (Cu)	<10	<10	<10	7700
Soluble Lead (Pb)	<10	<10	<10	23
Soluble Manganese (Mn)	<10	<10	<10	15000
Soluble Mercury (Hg)	<10	<10	<10	94
Soluble Nickel (Ni)	<10	<10	<10	930
Soluble Selenium (Se)	<10	<10	<10	460
Soluble Strontium (Sr)	<100	<100	<100	56000
Soluble Tin (Sn)	<10	<10	<10	180000
Soluble Organic tin ++	<5.0	<5.0	<5.0	12
Soluble Zinc (Zn)	400	450	470	46000







Number: HKGH0302244802

	Result (mg/kg)			Limit
	(7)	(8)	(9)	(mg/kg)
Soluble Aluminium (AI)	310	<300	560	28130
Soluble Antimony (Sb)	<10	<10	<10	560
Soluble Arsenic (As)	<10	<10	<10	47
Soluble Barium (Ba)	<10	<10	<10	18750
Soluble Boron (B)	<50	<50	<50	15000
Soluble Cadmium (Cd)	<5	<5	<5	17
Soluble Chromium (III) (Cr III)	<10	<10	<10	460
Soluble Chromium (VI) (Cr VI)	<0.025	<0.025	<0.025	0.053
Soluble Cobalt (Co)	<10	<10	<10	130
Soluble Copper (Cu)	<10	<10	<10	7700
Soluble Lead (Pb)	<10	<10	<10	23
Soluble Manganese (Mn)	<10	<10	<10	15000
Soluble Mercury (Hg)	<10	<10	<10	94
Soluble Nickel (Ni)	<10	<10	<10	930
Soluble Selenium (Se)	<10	<10	<10	460
Soluble Strontium (Sr)	<100	<100	<100	56000
Soluble Tin (Sn)	<10	<10	<10	180000
Soluble Organic tin ++	<5.0	<5.0	<5.0	12
Soluble Zinc (Zn)	410	<100	1600	46000





intertek.com.hk



		Result (mg/kg)		
	(10)	(11)	(12)	(mg/kg)
Soluble Aluminium (Al)	<300	<300	<300	28130
Soluble Antimony (Sb)	<10	<10	<10	560
Soluble Arsenic (As)	<10	<10	<10	47
Soluble Barium (Ba)	<10	<10	<10	18750
Soluble Boron (B)	<50	<50	<50	15000
Soluble Cadmium (Cd)	<5	<5	<5	17
Soluble Chromium (III) (Cr III)	<10	<10	<10	460
Soluble Chromium (VI) (Cr VI)	<0.025	<0.025	<0.025	0.053
Soluble Cobalt (Co)	<10	<10	<10	130
Soluble Copper (Cu)	<10	<10	<10	7700
Soluble Lead (Pb)	<10	<10	<10	23
Soluble Manganese (Mn)	<10	<10	<10	15000
Soluble Mercury (Hg)	<10	<10	<10	94
Soluble Nickel (Ni)	<10	<10	<10	930
Soluble Selenium (Se)	<10	<10	<10	460
Soluble Strontium (Sr)	<100	<100	<100	56000
Soluble Tin (Sn)	<10	<10	<10	180000
Soluble Organic tin ++	<5.0	<5.0	<5.0	12
Soluble Zinc (Zn)	<100	310	<100	46000







	Result (mg/kg)			Limit
	(13)	(14)	(15)	(mg/kg)
Soluble Aluminium (AI)	<300	<300	<300	28130
Soluble Antimony (Sb)	<10	<10	<10	560
Soluble Arsenic (As)	<10	<10	<10	47
Soluble Barium (Ba)	<10	<10	<10	18750
Soluble Boron (B)	<50	<50	<50	15000
Soluble Cadmium (Cd)	<5	<5	<5	17
Soluble Chromium (III) (Cr III)	<10	<10	<10	460
Soluble Chromium (VI) (Cr VI)	<0.025	<0.025	<0.025	0.053
Soluble Cobalt (Co)	<10	<10	<10	130
Soluble Copper (Cu)	<10	<10	<10	7700
Soluble Lead (Pb)	<10	<10	<10	23
Soluble Manganese (Mn)	<10	<10	<10	15000
Soluble Mercury (Hg)	<10	<10	<10	94
Soluble Nickel (Ni)	<10	<10	<10	930
Soluble Selenium (Se)	<10	<10	<10	460
Soluble Strontium (Sr)	<100	<100	<100	56000
Soluble Tin (Sn)	<10	<10	<10	180000
Soluble Organic tin ++	<5.0	<5.0	<5.0	12
Soluble Zinc (Zn)	<100	<100	<100	46000







		Result (mg/kg)		
	(16)	(17)	(18)	(mg/kg)
Soluble Aluminium (Al)	<300	<300	<300	28130
Soluble Antimony (Sb)	<10	<10	<10	560
Soluble Arsenic (As)	<10	<10	<10	47
Soluble Barium (Ba)	<10	<10	<10	18750
Soluble Boron (B)	<50	<50	<50	15000
Soluble Cadmium (Cd)	<5	<5	<5	17
Soluble Chromium (III) (Cr III)	<10	<10	<10	460
Soluble Chromium (VI) (Cr VI)	<0.025	<0.025	<0.025	0.053
Soluble Cobalt (Co)	<10	<10	<10	130
Soluble Copper (Cu)	<10	<10	<10	7700
Soluble Lead (Pb)	<10	<10	<10	23
Soluble Manganese (Mn)	<10	<10	<10	15000
Soluble Mercury (Hg)	<10	<10	<10	94
Soluble Nickel (Ni)	<10	<10	<10	930
Soluble Selenium (Se)	<10	<10	<10	460
Soluble Strontium (Sr)	<100	<100	<100	56000
Soluble Tin (Sn)	<10	<10	<10	180000
Soluble Organic tin ++	<5.0	<5.0	<5.0	12
Soluble Zinc (Zn)	<100	<100	<100	46000







		Result (mg/kg)		
	(19)	(20)	(21)	(mg/kg)
Soluble Aluminium (Al)	<300	<300	<300	28130
Soluble Antimony (Sb)	<10	<10	<10	560
Soluble Arsenic (As)	<10	<10	<10	47
Soluble Barium (Ba)	<10	<10	27	18750
Soluble Boron (B)	<50	<50	<50	15000
Soluble Cadmium (Cd)	<5	<5	<5	17
Soluble Chromium (III) (Cr III)	<10	<10	<10	460
Soluble Chromium (VI) (Cr VI)	<0.025	<0.025	<0.025	0.053
Soluble Cobalt (Co)	<10	<10	<10	130
Soluble Copper (Cu)	<10	<10	<10	7700
Soluble Lead (Pb)	<10	<10	<10	23
Soluble Manganese (Mn)	<10	<10	70	15000
Soluble Mercury (Hg)	<10	<10	<10	94
Soluble Nickel (Ni)	<10	<10	<10	930
Soluble Selenium (Se)	<10	<10	<10	460
Soluble Strontium (Sr)	<100	<100	<100	56000
Soluble Tin (Sn)	<10	<10	<10	180000
Soluble Organic tin ++	<5.0	<5.0	<5.0	12
Soluble Zinc (Zn)	<100	<100	<100	46000







Number: HKGH0302244802

	Result (mg/kg)	Limit
	(22)	(mg/kg)
Soluble Aluminium (AI)	<300	28130
Soluble Antimony (Sb)	<10	560
Soluble Arsenic (As)	<10	47
Soluble Barium (Ba)	<10	18750
Soluble Boron (B)	<50	15000
Soluble Cadmium (Cd)	<5	17
Soluble Chromium (III) (Cr III)	<10	460
Soluble Chromium (VI) (Cr VI)	<0.025	0.053
Soluble Cobalt (Co)	<10	130
Soluble Copper (Cu)	<10	7700
Soluble Lead (Pb)	<10	23
Soluble Manganese (Mn)	<10	15000
Soluble Mercury (Hg)	<10	94
Soluble Nickel (Ni)	<10	930
Soluble Selenium (Se)	<10	460
Soluble Strontium (Sr)	<100	56000
Soluble Tin (Sn)	<10	180000
Soluble Organic tin ++	<5.0	12
Soluble Zinc (Zn)	<100	46000

mg/kg = milligram per kilogram

Unless the test result was marked with " $\Delta$ ", Organic tin content was not directly determined and was derived from migration result of total tin.

Organic tin test result was expressed as tributyl tin.

Chromium (III) value was calculated as difference between migration results of total Chromium and Chromium (VÍ).







Number: HKGH0302244802

### **Tested Components:**

White coating on composite wood (handle, edge of racket). (1) (2) (3) (4) (5) (6) (7) (8) Beige coating on composite wood (base of pattern of racket). Yellow coating on composite wood (pattern of racket). Green coating on composite wood (pattern of racket). Sky blue coating on composite wood (pattern of racket). Pink coating on composite wood (pattern of racket). Orange coating on composite wood (pattern of racket). Black coating on composite wood (logo of racket). (9) Light blue coating on metal (D-ring, slider of zipper). Yellow plastic (ball). Grey foam (handle). (10)(11)White plastic (edge of bag). (12) (13)Dull white plastic (buckle). (14)Transparent plastic (bag). Plastic label with inaccessible dark grey printings (warning signal). (15)(16)Light blue plastic (puller). (17)Dull light blue plastic (zipper teeth). Light blue fabric (zipper tape). (18)White webbing (strap). (19) White fabric (edge of bag). (20)Composite wood excluding coatings (racket). Paper label with transparent plastic film (sticker on bag, racket).

Date sample received : Jun 13, 2023 Test Period : Jun 13, 2023 to Jun 27, 2023







Number: HKGH0302244802

#### (5)Cadmium (Cd) Content

Test Method : In House method TC008.TP. Acid digestion method was used and total Cadmium content was determined by Inductively Coupled Argon Plasma Spectrometry.

Tested Component	Result in %, w/w	Limit in %, w/w
(1/2/3)	ND	0.1
(4/5/6)	ND	0.1
(7/8)	ND	0.1
(9)	ND	0.1
(10/11/12)	ND	0.01
(13/14/15)	ND	0.01
(16/17)	ND	0.01
(18)	ND	0.01

ND Not detected (< 0.0005%)

The above limit was quoted according to Regulation (EC) No. 1907/2006 on REACH Annex XVII as amended by Commission Regulation (EU) No. 835/2012 and Commission Regulation (EU) 2016/217

### **Tested Components:**

- White coating on composite wood (handle, edge of racket).
- (2) (3) (4) (5) (6) (7) (8) (9) Beige coating on composite wood (base of pattern of racket).
- Yellow coating on composite wood (pattern of racket).
- Green coating on composite wood (pattern of racket).
- Sky blue coating on composite wood (pattern of racket).
- Pink coating on composite wood (pattern of racket).
- Orange coating on composite wood (pattern of racket).
- Black coating on composite wood (logo of racket).
- Light blue coating on metal (D-ring, slider of zipper).
- (10) Yellow plastic (ball).
- (11)Grey foam (handle).
- White plastic (edge of bag). (12)
- Dull white plastic (buckle). (13)
- Transparent plastic (bag). (14)
- Plastic label with inaccessible dark grey printings (warning signal).
- Light blue plastic (puller). (16)

Intertek Testing Services Hong Kong Limited

- Dull light blue plastic (zipper teeth).
- Paper label with transparent plastic film (sticker on bag, racket).





intertek.com.hk



Number: HKGH0302244802

Date sample received : Jun 13, 2023 Test Period : Jun 13, 2023 to Jun 27, 2023

### (6) Cadmium (Cd) Content

Test Method : In House method TC008.TP. Acid digestion method was used and total Cadmium

content was determined by Inductively Coupled Argon Plasma Spectrometry.

Tested Component	Result in %, w/w	Limit in %, w/w
(1/2/3)	ND	0.1
(4/5/6)	ND	0.1
(7/8)	ND	0.1
(9)	ND	0.1
(10/11/12)	ND	0.01
(13/14/15)	ND	0.01
(16/17)	ND	0.01
(18)	ND	0.01

ND : Not detected (< 0.0005%)

The above limit was quoted according to Annex XVII Entry 23 of the REACH Regulation (EC) No 1907/2006 and Amendment (EC) No 552/2009, (EU) No 494/2011, (EU) No 835/2012 and (EU) 2016/217 & The REACH etc. (Amendment etc.) (EU Exit) Regulations 2019 (S.I. 2019 No. 758)

### **Tested Components:**

- (1) White coating on composite wood (handle, edge of racket).
- (2) Beige coating on composite wood (base of pattern of racket).
- (3) Yellow coating on composite wood (pattern of racket).
- (4) Green coating on composite wood (pattern of racket).
- (5) Sky blue coating on composite wood (pattern of racket).
- (6) Pink coating on composite wood (pattern of racket).(7) Orange coating on composite wood (pattern of racket).
- (8) Black coating on composite wood (pattern of racket).
- (9) Light blue coating on metal (D-ring, slider of zipper).
- (2) Beige coating on cor (3) Yellow coating on cor (4) Green coating on co (5) Sky blue coating on (6) Pink coating on com (7) Orange coating on cor (8) Black coating on cor (9) Light blue coating or (10) Yellow plastic (ball).
- (11) Grey foam (handle).
- (12) White plastic (edge of bag).
- (13) Dull white plastic (buckle).
- (14) Transparent plastic (bag).
- (15) Plastic label with inaccessible dark grey printings (warning signal).
- (16) Light blue plastic (puller).
- (17) Dull light blue plastic (zipper teeth).
- (18) Paper label with transparent plastic film (sticker on bag, racket).







Number: HKGH0302244802

Date sample received : Jun 13, 2023 Test Period: Jun 13, 2023 to Jun 27, 2023

#### (7) Polycyclic Aromatic Hydrocarbons (PAH) Content

: The document AfPS GS 2019:01 PAK issued by the Federal Institute for Occupational Test Method

Safety and Health, solvent extraction and determined by Gas Chromatographic - Mass

Spectrometry (GC/MS).

Compound		Result (ppm)		
	(1/2/3)	(4/5/6)	(7/8)	(ppm)
Benzo(a)pyrene	<0.10	<0.10	<0.10	0.5
Benzo(e)pyrene	<0.10	<0.10	<0.10	0.5
Benzo(a)anthracene	<0.10	<0.10	<0.10	0.5
Chrysene	<0.10	<0.10	<0.10	0.5
Benzo(b)fluoranthene	<0.10	<0.10	<0.10	0.5
Benzo(j)fluoranthene	<0.10	<0.10	<0.10	0.5
Benzo(k)fluoranthene	<0.10	<0.10	<0.10	0.5
Dibenzo(a,h)anthracene	<0.10	<0.10	<0.10	0.5

Compound	Result (ppm)			
	(9)	(10/11/12)	(13/14/15)	(ppm)
Benzo(a)pyrene	<0.10	<0.10	<0.10	0.5
Benzo(e)pyrene	<0.10	<0.10	<0.10	0.5
Benzo(a)anthracene	<0.10	<0.10	<0.10	0.5
Chrysene	<0.10	<0.10	<0.10	0.5
Benzo(b)fluoranthene	<0.10	<0.10	<0.10	0.5
Benzo(j)fluoranthene	<0.10	<0.10	<0.10	0.5
Benzo(k)fluoranthene	<0.10	<0.10	<0.10	0.5
Dibenzo(a,h)anthracene	<0.10	<0.10	<0.10	0.5







Number: HKGH0302244802

Compound	Result (ppm)		
	(16/17)	(18)	(ppm)
Benzo(a)pyrene	<0.10	<0.10	0.5
Benzo(e)pyrene	<0.10	<0.10	0.5
Benzo(a)anthracene	<0.10	<0.10	0.5
Chrysene	<0.10	<0.10	0.5
Benzo(b)fluoranthene	<0.10	<0.10	0.5
Benzo(j)fluoranthene	<0.10	<0.10	0.5
Benzo(k)fluoranthene	<0.10	<0.10	0.5
Dibenzo(a,h)anthracene	<0.10	<0.10	0.5

The above limit was quoted according to Annex XVII Items 50 of the REACH Regulation (EC) no. 1907/2006 & amendment (EU) no. 1272/2013 for polycyclic aromatic hydrocarbons (PAH).

ppm = parts per million = mg/kg

### **Tested Components:**

- White coating on composite wood (handle, edge of racket). Beige coating on composite wood (base of pattern of racket). (2) (3) (4) (5) (6) (7) (8)
- Yellow coating on composite wood (pattern of racket).
- Green coating on composite wood (pattern of racket).
- Sky blue coating on composite wood (pattern of racket).
- Pink coating on composite wood (pattern of racket). Orange coating on composite wood (pattern of racket).
- Black coating on composite wood (logo of racket).
- (e) Light blue coating on metal (D-ring, slider of zipper).
- Yellow plastic (ball).
- Grey foam (handle).
- White plastic (edge of bag). (12) (13)
- Dull white plastic (buckle).
- Transparent plastic (bag).
- Plastic label with inaccessible dark grey printings (warning signal). (15)
- Light blue plastic (puller). (16)
- Dull light blue plastic (zipper teeth).
- Paper label with transparent plastic film (sticker on bag, racket). (18)

Date sample received: Jun 13, 2023 Test Period: Jun 13, 2023 to Jun 23, 2023





Kowloon, Hong Kong



Number: HKGH0302244802

### (8) Polycyclic Aromatic Hydrocarbons (PAH) Content

Test Method : The document AfPS GS 2019:01 PAK issued by the Federal Institute for Occupational

Safety and Health, solvent extraction and determined by Gas Chromatographic - Mass

Spectrometry (GC/MS).

Compound		Result (ppm)		
	(1/2/3)	(4/5/6)	(7/8)	(ppm)
Benzo(a)pyrene	<0.10	<0.10	<0.10	0.5
Benzo(e)pyrene	<0.10	<0.10	<0.10	0.5
Benzo(a)anthracene	<0.10	<0.10	<0.10	0.5
Chrysene	<0.10	<0.10	<0.10	0.5
Benzo(b)fluoranthene	<0.10	<0.10	<0.10	0.5
Benzo(j)fluoranthene	<0.10	<0.10	<0.10	0.5
Benzo(k)fluoranthene	<0.10	<0.10	<0.10	0.5
Dibenzo(a,h)anthracene	<0.10	<0.10	<0.10	0.5

Compound	Result (ppm)			Limit
	(9)	(10/11/12)	(13/14/15)	(ppm)
Benzo(a)pyrene	<0.10	<0.10	<0.10	0.5
Benzo(e)pyrene	<0.10	<0.10	<0.10	0.5
Benzo(a)anthracene	<0.10	<0.10	<0.10	0.5
Chrysene	<0.10	<0.10	<0.10	0.5
Benzo(b)fluoranthene	<0.10	<0.10	<0.10	0.5
Benzo(j)fluoranthene	<0.10	<0.10	<0.10	0.5
Benzo(k)fluoranthene	<0.10	<0.10	<0.10	0.5
Dibenzo(a,h)anthracene	<0.10	<0.10	<0.10	0.5

Compound	Resul	Limit	
	(16/17)	(18)	(ppm)
Benzo(a)pyrene	<0.10	<0.10	0.5
Benzo(e)pyrene	<0.10	<0.10	0.5
Benzo(a)anthracene	<0.10	<0.10	0.5
Chrysene	<0.10	<0.10	0.5
Benzo(b)fluoranthene	<0.10	<0.10	0.5
Benzo(j)fluoranthene	<0.10	<0.10	0.5
Benzo(k)fluoranthene	<0.10	<0.10	0.5
Dibenzo(a,h)anthracene	<0.10	<0.10	0.5







Number: HKGH0302244802

The above limit was quoted according to REACH Regulation (EC) no. 1907/2006 & amendment no. 1272/2013, Annex XVII, Item 50 & The REACH etc. (Amendment etc.) (EU Exit) Regulations 2019 (S.I. 2019 No. 758) as amended for polycyclic aromatic hydrocarbons (PAH).

ppm = parts per million = mg/kg

### **Tested Components:**

- White coating on composite wood (handle, edge of racket). (2) (3) (4) (5) (6) (7) (8) (9) Beige coating on composite wood (base of pattern of racket). Yellow coating on composite wood (pattern of racket). Green coating on composite wood (pattern of racket). Sky blue coating on composite wood (pattern of racket). Pink coating on composite wood (pattern of racket). Orange coating on composite wood (pattern of racket). Black coating on composite wood (logo of racket). Light blue coating on metal (D-ring, slider of zipper). (10) Yellow plastic (ball).
- (11) Grey foam (handle).
- White plastic (edge of bag). Dull white plastic (buckle). (12)(13)Transparent plastic (bag).
- (15) Plastic label with inaccessible dark grey printings (warning signal).
- Light blue plastic (puller). (16)
- Dull light blue plastic (zipper teeth). (17)
- (18)Paper label with transparent plastic film (sticker on bag, racket).

Date sample received: Jun 13, 2023 Test Period: Jun 13, 2023 to Jun 23, 2023







Number: HKGH0302244802

### (9) Phthalate Content Test

Test Method : ISO 8124-6 : 2018 method A with internal standard calibration, by Gas

Chromatographic-Mass Spectrometric (GC-MS) analysis.

### Seven Phthalates content:

Compound	Result (%, w/w)			Limit (%,
	(1)	(2)	(3/4/5)	w/w)
Dibutyl phthalate (DBP)	<0.0100	<0.0100	<0.0100	
Diethyl hexyl phthalate (DEHP)	<0.0100	<0.0100	<0.0100	
Benzyl butyl phthalate (BBP)	<0.0100	<0.0100	<0.0100	
Diisobutyl phthalate (DIBP)	<0.0100	<0.0100	<0.0100	
Sum of DBP, DEHP, BBP & DIBP	<0.0100	<0.0100	<0.0100	0.1
Diisononyl phthalate (DINP)	<0.0100	<0.0100	<0.0100	
Di-n-octyl phthalate (DnOP)	<0.0100	<0.0100	<0.0100	
Diisodecyl phthalate (DIDP)	<0.0100	<0.0100	<0.0100	
Sum of DINP, DnOP & DIDP	<0.0100	<0.0100	<0.0100	0.1

Compound		Result (%, w/w)		
	(6/7/8)	(9/10)	(11)	w/w)
Dibutyl phthalate (DBP)	<0.0100	<0.0100	<0.0100	
Diethyl hexyl phthalate (DEHP)	<0.0100	<0.0100	<0.0100	
Benzyl butyl phthalate (BBP)	<0.0100	<0.0100	<0.0100	
Diisobutyl phthalate (DIBP)	<0.0100	<0.0100	<0.0100	
Sum of DBP, DEHP, BBP & DIBP	<0.0100	<0.0100	<0.0100	0.1
Diisononyl phthalate (DINP)	<0.0100	<0.0100	<0.0100	
Di-n-octyl phthalate (DnOP)	<0.0100	<0.0100	<0.0100	
Diisodecyl phthalate (DIDP)	<0.0100	<0.0100	<0.0100	
Sum of DINP, DnOP & DIDP	<0.0100	<0.0100	<0.0100	0.1







Number: HKGH0302244802

The above limit was quoted according to Annex XVII Items 51 & 52 of the REACH Regulation (EC) no. 1907/2006, amendment no. 552/2009 taking into account the (EU) regulation 2018/2005 modifying entry 51 for which the DIBP shall not be placed on the market after 7 July 2020 in toys or childcare articles, individually or in any combination with the first three phthalates which already exist in the entry 51, in a concentration equal to or greater than 0,1 % by weight of the plasticised material.

### **Tested Components:**

- Light blue coating on metal (D-ring, slider of zipper).
- Coatings on composite wood (racket).
- Yellow plastic (ball).
- Grey foam (handle).
- White plastic (edge of bag). Dull white plastic (buckle).
- (2) (3) (4) (5) (6) (7) Transparent plastic (bag).
- (8) Plastic label with inaccessible dark grey printings (warning signal).
- (9) Light blue plastic (puller).
- (10)Dull light blue plastic (zipper teeth).
- Paper label with transparent plastic film (sticker on bag, racket).

Date sample received: Jun 13, 2023 Test Period: Jun 13, 2023 to Jun 23, 2023







Number: HKGH0302244802

### (10) Phthalate Content Test

Test Method : ISO 8124-6 : 2018 method A with internal standard calibration, by Gas

Chromatographic-Mass Spectrometric (GC-MS) analysis.

### Seven Phthalates content:

Compound		Limit (%,		
	(1)	(2)	(3/4/5)	w/w)
Dibutyl phthalate (DBP)	<0.0100	<0.0100	<0.0100	
Diethyl hexyl phthalate (DEHP)	<0.0100	<0.0100	<0.0100	
Benzyl butyl phthalate (BBP)	<0.0100	<0.0100	<0.0100	
Diisobutyl phthalate (DIBP)	<0.0100	<0.0100	<0.0100	
Sum of DBP, DEHP, BBP & DIBP	<0.0100	<0.0100	<0.0100	0.1
Diisononyl phthalate (DINP)	<0.0100	<0.0100	<0.0100	
Di-n-octyl phthalate (DnOP)	<0.0100	<0.0100	<0.0100	
Diisodecyl phthalate (DIDP)	<0.0100	<0.0100	<0.0100	
Sum of DINP, DnOP & DIDP	<0.0100	<0.0100	<0.0100	0.1

Compound	Result (%, w/w)			Limit (%,
	(6/7/8)	(9/10)	(11)	w/w)
Dibutyl phthalate (DBP)	<0.0100	<0.0100	<0.0100	
Diethyl hexyl phthalate (DEHP)	<0.0100	<0.0100	<0.0100	
Benzyl butyl phthalate (BBP)	<0.0100	<0.0100	<0.0100	
Diisobutyl phthalate (DIBP)	<0.0100	<0.0100	<0.0100	
Sum of DBP, DEHP, BBP & DIBP	<0.0100	<0.0100	<0.0100	0.1
Diisononyl phthalate (DINP)	<0.0100	<0.0100	<0.0100	
Di-n-octyl phthalate (DnOP)	<0.0100	<0.0100	<0.0100	
Diisodecyl phthalate (DIDP)	<0.0100	<0.0100	<0.0100	
Sum of DINP, DnOP & DIDP	<0.0100	<0.0100	<0.0100	0.1





Kowloon, Hong Kong



Number: HKGH0302244802

The above limit was quoted according to REACH Regulation (EC) no. 1907/2006, Annex XVII, Item 51 & 52 & amendment no. 552/2009 & 2018/2005 & The REACH etc. (Amendment etc.) (EU Exit) Regulations 2019 (S.I. 2019 No. 758) as amended.

### **Tested Components:**

- Light blue coating on metal (D-ring, slider of zipper).
- Coatings on composite wood (racket).
- (1) (2) (3) (4) (5) (6) (7) (8) Yellow plastic (ball).
- Grey foam (handle).
- White plastic (edge of bag). Dull white plastic (buckle).
- Transparent plastic (bag).
- Plastic label with inaccessible dark grey printings (warning signal).
- (9) Light blue plastic (puller).
- Dull light blue plastic (zipper teeth).
- Paper label with transparent plastic film (sticker on bag, racket).

Date sample received: Jun 13, 2023 Test Period: Jun 13, 2023 to Jun 23, 2023







Number: HKGH0302244802



End of report

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to and subject to our standard Terms and Conditions which can be obtained at our website: <a href="http://www.intertek.com/terms/">http://www.intertek.com/terms/</a>. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Intertek is responsible for all the information provided in the reports, except when information is provided by the Client or when the Client requires the item to be tested acknowledging a deviation from specified conditions that can affect the validity of results.

The observations and test results in this report are relevant to the sample(s) tested and submitted by client. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. This report does not discharge or release you from your legal obligations and duties to any other person. Only the Client is authorized to permit copying or distribution of this report and the report shall not be reproduced except in full. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.



